

OIL ANALYSIS REPORT

Sample Rating Trend





Machine Id 913024 Component

Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- GAL)

N SHP 15W40 (-	GAL)	Nov2022 J:	m2023 Feb2023 Mar	2023 Apr2023 May2023	Jun2023	
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0068755	GFL0068721	GFL0068942
Sample Date		Client Info		10 Jul 2023	19 Jun 2023	05 Jun 2023
Machine Age	hrs	Client Info		2774	2644	2525
Oil Age	hrs	Client Info		371	241	122
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	ATTENTION	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	0.0	NEG
WEAR METAL	.S	method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>120	10	29	4
Chromium	ppm	ASTM D5185m	>20	<1	1	<1
Nickel	ppm	ASTM D5185m	>5	1	<1	<1
Titanium	ppm	ASTM D5185m	>2	<1	<1	<1
Silver	ppm	ASTM D5185m	>2	<1	0	0
Aluminum	ppm	ASTM D5185m	>20	1	5	<1
Lead	ppm	ASTM D5185m	>40	<1	1	0
Copper	ppm	ASTM D5185m	>330	2	49	<1
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	6	10	6
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	66	69	65
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Vagnesium	ppm	ASTM D5185m	1010	1005	837	958
Calcium	ppm	ASTM D5185m	1070	1147	1038	1131
Phosphorus	ppm	ASTM D5185m	1150	1060	944	989
Zinc	ppm	ASTM D5185m	1270	1339	1151	1231
Sulfur	ppm	ASTM D5185m	2060	3769	3557	3678
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5	11	4
Sodium	ppm	ASTM D5185m		3	2 54	2
Potassium	ppm	ASTM D5185m	>20	2	4	<1
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>4	0.5	0.3	0.2
Nitration	Abs/cm	*ASTM D7624	>20	8.7	9.4	6.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.0	20.8	18.8
FLUID DEGRA		method	limit/base	ourropt	history1	history2
I LOID DEGINA		method	iiiiii/base	current	history i	That of yz
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.6	16.7	14.3

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.




Jan 16/23


Ĕ.

Feb27/23

OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.5	13.9	13.6
GRAPHS						
Ferrous Alloys						
30 iron 1			A			
25 - newspace chromium			A			
20-						
15-			1			



Apr25/23

May22/23

Jun 19/23

10

4/22

an 16/23

Aar20.07

Anr75/73

av22/2:

