

## **OIL ANALYSIS REPORT**

Sample Rating Trend

NORMAL

# NORTH SIDE SHIPPING BRIDGE

**Gearbox** 

### SCHAEFFER MOLY FULL SYN GEAR OIL (--- GAL)

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


#### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

•)				Jul2023		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0100298		
Sample Date		Client Info		16 Jul 2023		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METAL	.S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	158		
Chromium	ppm	ASTM D5185m	>15	1		
Nickel	ppm	ASTM D5185m	>15	<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	3		
Lead	ppm	ASTM D5185m	>100	0		
Copper	ppm	ASTM D5185m		2		
Tin	ppm	ASTM D5185m	>25	0		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES	1- 1-	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		60		
Barium	ppm	ASTM D5185m		0		
Volybdenum		ASTM D5185m		477		
	ppm	ASTM D5185m		2		
Manganese	ppm					
Magnesium	ppm	ASTM D5185m		3		
Calcium	ppm	ASTM D5185m		44		
Phosphorus	ppm	ASTM D5185m		1180		
Zinc	ppm	ASTM D5185m		36		
Sulfur	ppm	ASTM D5185m		25056		
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	31		
Sodium	ppm	ASTM D5185m		5		
Potassium	ppm	ASTM D5185m	>20	<1		
FLUID DEGRAI	DATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		2.39		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	LIGHT		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		
36:00) Rev: 1					cation: BYAN C	



## **OIL ANALYSIS REPORT**



225 Visc @ 40°C cSt ASTM D445 SAMPLE IMAGES no image no image Bottom no image no image GRAPHS Ferrous Alloys nickel Non-ferrous Metals lead ppm Viscosity @ 40°C Acid Number 245 Abnormal 2. 240 23 2.0 230 (mg KOH/g) () 225 0€ 220 1.5 Number 1.0 . 경<sub>215</sub> 210 Acid 205 0.5 200 Abnorma 195 0.0 Jul16/23 Jul16/23 NATIONAL MATERIAL PROCESSING Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. : PCA0100298 Received : 17 Jul 2023 4506 CLINE AVE Lab Number : 05900108 Diagnosed : 18 Jul 2023 EAST CHICAGO, IN Unique Number : 10561464 Diagnostician : Wes Davis US 46312 Test Package : IND 2 Contact: RYAN CANO To discuss this sample report, contact Customer Service at 1-800-237-1369. rcano@nmlp.com \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Т: Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F:

Certificate L2367

Contact/Location: RYAN CANO - NATEAS