

## **OIL ANALYSIS REPORT**

### 10963 FREIGHTLINER Component

**Diesel Engine** 

#### Fluic PETRO CANADA DURON SHP 15W40 (42 QTS)

### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.






NORMAL


Sample Rating Trend

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0087129	GFL0056684	GFL0056671
Sample Date		Client Info		17 Jul 2023	13 Apr 2023	26 Jan 2023
Machine Age	hrs	Client Info		16278	15712	15295
Oil Age	hrs	Client Info		566	417	656
Oil Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATI	ON	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>75	24	22	27
Chromium	ppm	ASTM D5185m	>5	1	1	1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>15	3	0	3
Lead	ppm	ASTM D5185m	>25	2	<1	<1
Copper	ppm	ASTM D5185m	>100	-	<1	1
Tin	ppm	ASTM D5185m	>4	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method				history2
ADDITIVES Boron	ppm	method ASTM D5185m	limit/base		history1 4	
	ppm ppm		0	current 3 0		history2 6 0
Boron	ppm ppm ppm	ASTM D5185m	0	3	4	6
Boron Barium Molybdenum	ppm	ASTM D5185m ASTM D5185m	0 0 60	3 0	4	6 0
Boron Barium	ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m	0 0 60	3 0 65	4 0 60	6 0 62
Boron Barium Molybdenum Manganese	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	0 0 60 0	3 0 65 <1	4 0 60 <1	6 0 62 <1
Boron Barium Molybdenum Manganese Magnesium	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	0 0 60 0 1010	3 0 65 <1 1022	4 0 60 <1 895	6 0 62 <1 912
Boron Barium Molybdenum Manganese Magnesium Calcium	ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	0 0 60 0 1010 1070	3 0 65 <1 1022 1157	4 0 60 <1 895 1034	6 0 62 <1 912 1046
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus	ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	0 0 60 0 1010 1070 1150	3 0 65 <1 1022 1157 1089	4 0 60 <1 895 1034 972	6 0 62 <1 912 1046 924
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc	ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	0 0 60 0 1010 1070 1150 1270	3 0 65 <1 1022 1157 1089 1325	4 0 60 <1 895 1034 972 1211	6 0 62 <1 912 1046 924 1235
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur	ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	0 0 60 1010 1070 1150 1270 2060 limit/base	3 0 65 <1 1022 1157 1089 1325 3661	4 0 60 <1 895 1034 972 1211 2794	6 0 62 <1 912 1046 924 1235 3287
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN	ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	0 0 60 1010 1070 1150 1270 2060 limit/base	3 0 65 <1 1022 1157 1089 1325 3661 current	4 0 60 <1 895 1034 972 1211 2794 history1	6 0 62 <1 912 1046 924 1235 3287 history2
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon	ppm ppm ppm ppm ppm ppm ppm ppm TS	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m <b>method</b>	0 0 60 0 1010 1070 1150 1270 2060 limit/base >25	3 0 65 <1 1022 1157 1089 1325 3661 <i>current</i> 14	4 0 60 <1 895 1034 972 1211 2794 history1 5	6 0 62 <1 912 1046 924 1235 3287 history2 5
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium	ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m <b>method</b> ASTM D5185m	0 0 60 0 1010 1070 1150 1270 2060 limit/base >25	3 0 65 <1 1022 1157 1089 1325 3661 <u>current</u> 14 7	4 0 60 <1 895 1034 972 1211 2794 history1 5 8	6 0 62 <1 912 1046 924 1235 3287 history2 5 8
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium	ppm	ASTM D5185m ASTM D5185m	0 0 60 1010 1070 1150 1270 2060 limit/base >25 >20	3 0 65 <1 1022 1157 1089 1325 3661 <u>current</u> 14 7 2	4 0 60 <1 895 1034 972 1211 2794 history1 5 8 2	6 0 62 <1 912 1046 924 1235 3287 history2 5 8 1
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium	ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m	0 0 0 1010 1070 1150 1270 2060 imit/base >25 >20 imit/base >6	3 0 65 <1 1022 1157 1089 1325 3661 <u>current</u> 14 7 2 2	4 0 60 <1 895 1034 972 1211 2794 history1 5 8 2 2 history1	6 0 62 <1 912 1046 924 1235 3287 history2 5 8 1 1 history2
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium INFRA-RED Soot %	ppm	ASTM D5185m ASTM D5185m	0 0 0 1010 1070 1150 1270 2060 imit/base >25 20 imit/base >6 >20	3 0 65 <1 1022 1157 1089 1325 3661 <i>current</i> 14 7 2 <i>current</i> 0.5	4 0 60 <1 895 1034 972 1211 2794 history1 5 8 2 2 history1 0.4	6 0 62 <1 912 1046 924 1235 3287 history2 5 8 1 1 history2 0.5
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Zinc Sulfur CONTAMINAN Silicon Sodium Potassium INFRA-RED Soot % Nitration	ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m	0 0 0 1010 1070 1150 1270 2060 imit/base >25 20 imit/base >6 >20	3 0 65 <1 1022 1157 1089 1325 3661 <i>current</i> 14 7 2 2 <i>current</i> 0.5 11.3	4 0 60 <1 895 1034 972 1211 2794 history1 5 8 2 2 history1 0.4 10.3	6 0 62 <1 912 1046 924 1235 3287 history2 5 8 1 1 history2 0.5 11.7
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc Sulfur CONTAMINAN Silicon Sodium Potassium INFRA-RED Soot % Nitration Sulfation	ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m	0 0 1010 1070 1150 1270 2060 <b>imit/base</b> >25 <b>imit/base</b> >20 <b>imit/base</b> >6 >20	3 0 65 <1 1022 1157 1089 1325 3661 <u>current</u> 14 7 2 2 <u>current</u> 0.5 11.3 22.5	4 0 60 <1 895 1034 972 1211 2794 history1 5 8 2 history1 0.4 10.3 21.6	6 0 62 <1 912 1046 924 1235 3287 history2 5 8 1 1 history2 0.5 11.7 23.0




# **OIL ANALYSIS REPORT**





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.3	13.8	14.0
GRAPHS						





 Certificate L2367
 Test Package
 : FLEET

 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 \*

 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Submitted By: Craig Johnson

craig.johnson@gflenv.com

T: (919)662-7100

F: (919)662-7130

Page 2 of 2