




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
413059

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0085494	GFL0085459	GFL0078214
Sample Date	Client Info		13 Jul 2023	09 Jun 2023	04 Jun 2023
Machine Age	mls	Client Info	42909	48976	0
Oil Age	mls	Client Info	42909	33088	0
Oil Changed	Client Info		Changed	Changed	N/A
Sample Status			NORMAL	NORMAL	ABNORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	<1.0	0.4
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >100	8	9	51
Chromium	ppm	ASTM D5185m >20	0	0	1
Nickel	ppm	ASTM D5185m >4	0	0	5
Titanium	ppm	ASTM D5185m	0	0	0
Silver	ppm	ASTM D5185m >3	0	0	0
Aluminum	ppm	ASTM D5185m >20	6	1	19
Lead	ppm	ASTM D5185m >40	<1	1	<1
Copper	ppm	ASTM D5185m >330	2	2	123
Tin	ppm	ASTM D5185m >15	0	0	4
Vanadium	ppm	ASTM D5185m	0	<1	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	0	0	168
Barium	ppm	ASTM D5185m 0	0	0	0
Molybdenum	ppm	ASTM D5185m 60	43	44	116
Manganese	ppm	ASTM D5185m 0	<1	<1	4
Magnesium	ppm	ASTM D5185m 1010	10	7	698
Calcium	ppm	ASTM D5185m 1070	2618	2925	1468
Phosphorus	ppm	ASTM D5185m 1150	1071	1161	656
Zinc	ppm	ASTM D5185m 1270	1254	1458	826
Sulfur	ppm	ASTM D5185m 2060	3401	4107	2587

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	7	8	▲ 76
Sodium	ppm	ASTM D5185m	0	<1	5
Potassium	ppm	ASTM D5185m >20	15	14	56

INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.2	0.2	0.4
Nitration	Abs/cm	*ASTM D7624 >20	8.3	8.2	10.4
Sulfation	Abs/.1mm	*ASTM D7415 >30	18.4	19.3	25.0

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	10.3	10.1	24.1
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	7.3	8.4	7.3







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.5	14.7 ▲ 9.9

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0085494 **Received** : 19 Jul 2023
Lab Number : 05902760 **Diagnosed** : 21 Jul 2023
Unique Number : 10564116 **Diagnostician** : Sean Felton
Test Package : FLEET

GFL Environmental - 983 - Sugar Land Hauling
 16011 West Belfort Street
 Sugar Land, TX
 US 77498
 Contact: Gino Griego
 ggriego@gflenv.com
 T:
 F:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)