

OIL ANALYSIS REPORT

Sample Rating Trend

FUEL

KAWASAKI 95Z KAWASAKI 95Z Component

DIESEL ENGINE OIL SAE 15W40 (--- GAL)

DIAGNOSIS

Recommendation

We advise that you check the fuel injection system. We recommend that you drain the oil and perform a filter service on this component if not already done. We recommend an early resample to monitor this condition.

Wear

All component wear rates are normal.

Contamination

There is a high amount of fuel present in the oil.


Fluid Condition


Fuel is present in the oil and is lowering the viscosity. The BN result indicates that there is suitable alkalinity remaining in the oil. The oil is no longer serviceable due to the presence of contaminants.


				Aug2023		
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0090963		
Sample Date		Client Info		02 Aug 2023		
Machine Age	hrs	Client Info		166		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				SEVERE		
CONTAMINAT	ION	method	limit/base	current	history1	history2
Glycol		WC Method		NEG		
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	9		
Chromium	ppm	ASTM D5185m	>20	2		
Nickel	ppm	ASTM D5185m	>4	0		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m		<1		
Lead	ppm	ASTM D5185m	>40	3		
Copper	ppm	ASTM D5185m	>330	9		
Tin	ppm	ASTM D5185m	>15	1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	250	4		
Barium	ppm	ASTM D5185m	10	0		
Molybdenum	ppm	ASTM D5185m	100	34		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m	450	582		
Calcium	ppm	ASTM D5185m	3000	685		
Phosphorus	ppm	ASTM D5185m	1150	651		
Zinc	ppm	ASTM D5185m	1350	766		
Sulfur	ppm	ASTM D5185m	4250	2350		
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	4		
Sodium	ppm	ASTM D5185m	>158	9		
Potassium	ppm	ASTM D5185m	>20	2		
Fuel	%	ASTM D3524	>5	• 45.1		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.1		
Nitration	Abs/cm	*ASTM D7624	>20	7.5		
Sulfation	Abs/.1mm	*ASTM D7415	>30	15.5		
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	11.2		
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	9.2		
	9.09			-		





OIL ANALYSIS REPORT











Laboratory

Sample No.

Lab Number

T: F:

Contact: Service Manager