




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
788M

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0081246	GFL0081301	GFL0071185
Sample Date	Client Info	04 Aug 2023	22 May 2023	16 Mar 2023
Machine Age	hrs	16757	16136	15538
Oil Age	hrs	600	600	600
Oil Changed	Client Info	Changed	Changed	Changed
Sample Status		NORMAL	NORMAL	ATTENTION

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >5	<1.0	<1.0	<1.0
Glycol	WC Method	NEG	0.0	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >100	42	35	33
Chromium	ppm ASTM D5185m >20	2	2	1
Nickel	ppm ASTM D5185m >4	0	<1	<1
Titanium	ppm ASTM D5185m	0	<1	<1
Silver	ppm ASTM D5185m >3	<1	<1	0
Aluminum	ppm ASTM D5185m >20	4	3	6
Lead	ppm ASTM D5185m >40	2	2	<1
Copper	ppm ASTM D5185m >330	2	5	23
Tin	ppm ASTM D5185m >15	<1	<1	<1
Vanadium	ppm ASTM D5185m	0	<1	<1
Cadmium	ppm ASTM D5185m	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 0	2	3	4
Barium	ppm ASTM D5185m 0	0	0	0
Molybdenum	ppm ASTM D5185m 60	72	67	67
Manganese	ppm ASTM D5185m 0	<1	1	<1
Magnesium	ppm ASTM D5185m 1010	1023	1077	935
Calcium	ppm ASTM D5185m 1070	1247	1199	1149
Phosphorus	ppm ASTM D5185m 1150	1118	1078	1006
Zinc	ppm ASTM D5185m 1270	1369	1387	1265
Sulfur	ppm ASTM D5185m 2060	3086	3189	2805

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >25	8	7	6
Sodium	ppm ASTM D5185m	55	93	▲ 139
Potassium	ppm ASTM D5185m >20	2	2	2

INFRA-RED



method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >3	1.8	1.3	1.2
Nitration	Abs/cm *ASTM D7624 >20	10.7	10.5	10.5
Sulfation	Abs/.1mm *ASTM D7415 >30	24.1	24.2	22.6

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	19.1	19.5	17.9
Base Number (BN)	mg KOH/g ASTM D2896 9.8	7.5	7.7	8.1







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	14.9	14.3	14.1

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0081246 **Received** : 09 Aug 2023
Lab Number : **05920045** **Diagnosed** : 10 Aug 2023
Unique Number : 10591959 **Diagnostician** : Wes Davis
Test Package : FLEET

GFL Environmental - 465 - Pontiac
 888 Baldwin
 Pontiac, MI
 US 48340
 Contact: Ricky Matthews
 rickymathews@gflenv.com
 T: (586)825-9514
 F:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)