OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Machine Id
PC DURON HP 15W40 DRUM - PCA05920951
Component
New (Unused) Oil
Fluid
{not provided} (--- GAL)

DIAGNOSIS

Recommendation
This is a baseline read-out on the submitted sample.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**PCA05920951**	---	---
Sample Date		Client Info		**09 Aug 2023**	---	---
Machine Age	hrs	Client Info		**0**	---	---
Oil Age	hrs	Client Info		**0**	---	---
Oil Changed		Client Info		**N/A**	---	---
Sample Status				**NORMAL**	---	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>5	**<1**	---	---
Chromium	ppm	ASTM D5185m	>5	**<1**	---	---
Nickel	ppm	ASTM D5185m	>5	**0**	---	---
Titanium	ppm	ASTM D5185m		**0**	---	---
Silver	ppm	ASTM D5185m	>5	**0**	---	---
Aluminum	ppm	ASTM D5185m	>5	**0**	---	---
Lead	ppm	ASTM D5185m	>5	**0**	---	---
Copper	ppm	ASTM D5185m	>5	**0**	---	---
Tin	ppm	ASTM D5185m	>5	**0**	---	---
Vanadium	ppm	ASTM D5185m		**0**	---	---
Cadmium	ppm	ASTM D5185m		**0**	---	---

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		**0**	---	---
Barium	ppm	ASTM D5185m		**1**	---	---
Molybdenum	ppm	ASTM D5185m		**58**	---	---
Manganese	ppm	ASTM D5185m		**0**	---	---
Magnesium	ppm	ASTM D5185m		**940**	---	---
Calcium	ppm	ASTM D5185m		**1032**	---	---
Phosphorus	ppm	ASTM D5185m		**1001**	---	---
Zinc	ppm	ASTM D5185m		**1178**	---	---
Sulfur	ppm	ASTM D5185m		**3163**	---	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	**4**	---	---
Sodium	ppm	ASTM D5185m		**2**	---	---
Potassium	ppm	ASTM D5185m	>20	**<1**	---	---

FLUID DEGRADATION		method	limit/base	current	history1	history2
Base Number (BN)	mg KOH/g	ASTM D2896		**10.42**	---	---

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	---	---
Yellow Metal	scalar	*Visual	NONE	**NONE**	---	---
Precipitate	scalar	*Visual	NONE	**NONE**	---	---
Silt	scalar	*Visual	NONE	**NONE**	---	---
Debris	scalar	*Visual	NONE	**NONE**	---	---
Sand/Dirt	scalar	*Visual	NONE	**NONE**	---	---
Appearance	scalar	*Visual	NORML	**NORML**	---	---
Odor	scalar	*Visual	NORML	**NORML**	---	---
Emulsified Water	scalar	*Visual		**NEG**	---	---
Free Water	scalar	*Visual		**NEG**	---	---

OIL ANALYSIS REPORT

Base Number

Viscosity @ 100°C



Viscosity @ 40°C



Acid Number



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		**116.8**	---	---
Visc @ 100°C	cSt	ASTM D445		**15.55**	---	---
Viscosity Index (VI)	Scale	ASTM D2270		**140**	---	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				*no image*	*no image*
Bottom				*no image*	*no image*

GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 40°C



Acid Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA05920951
Lab Number : 05920951
Unique Number : 10592865
Test Package : MOB 2 (Additional Tests: FT-IR, ICP-NewOil, KF, KV100, PrtCount, TBN, VI)

Received : 10 Aug 2023
Diagnosed : 11 Aug 2023
Diagnostician : Jonathan Hester

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

PETRO CANADA AMERICA LUBRRICANTS INC
MISSISSAUGA, ON
US
Contact: Jason Schaben
Jason.schaben@HFSinclair.com
T:
F: