


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id **427183 - SW4723**

Component **Diesel Engine**

PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

ARL)		Feb 202	3 Apr2023	Jul2023 Ax	ug2023	
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0089375	GFL0085407	GFL0075392
Sample Date		Client Info		09 Aug 2023	06 Jul 2023	19 Apr 2023
Machine Age	mls	Client Info		298070	293632	283804
Oil Age	mls	Client Info		298070	0	283804
Oil Changed		Client Info		Changed	N/A	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	7	15	15
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	1	1
Lead	ppm	ASTM D5185m	>40	2	4	<1
Copper	ppm	ASTM D5185m	>330	<1	2	3
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	<1	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0	3
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	39	42	43
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	1010	8	18	91
Calcium	ppm	ASTM D5185m	1070	2403	2578	2896
Phosphorus	ppm	ASTM D5185m	1150	1011	1074	1124
Zinc	ppm	ASTM D5185m	1270	1163	1287	1377
Sulfur	ppm	ASTM D5185m	2060	3127	3802	3554
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	9	12	16
Sodium	ppm	ASTM D5185m		<1	2	4
Potassium	ppm	ASTM D5185m	>20	1	1	0
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.2	0.3	0.3
Nitration	Abs/cm	*ASTM D7624	>20	7.2	9.6	8.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.5	22.5	19.8
FLUID DEGRA	OATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	10.4	13.0	11.7
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	5.2	6.6	7.2
. ,	- 0					



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPERTIES		method				history2	
Visc @ 100°C	cSt	ASTM D445	15.4	13.3	13.6	13.0	

GRAPHS













Certificate L2367

Laboratory Sample No. Lab Number Test Package : FLEET

Unique Number : 10604649

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0089375 : 05924702

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received

: 15 Aug 2023 Diagnosed : 16 Aug 2023 Diagnostician : Sean Felton

GFL Environmental - 983 - Sugar Land Hauling

16011 West Belfort Street Sugar Land, TX US 77498 Contact: Gino Griego

ggriego@gflenv.com T:

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: