




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
710022

Component
Diesel Engine

Fluid
DIESEL ENGINE OIL SAE 40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0083844	GFL0061475	GFL0047857
Sample Date	Client Info	03 Aug 2023	08 May 2023	28 Jul 2022
Machine Age	hrs	3901	3901	3901
Oil Age	hrs	3901	3901	600
Oil Changed	Client Info	N/A	N/A	Changed
Sample Status		NORMAL	ABNORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >5	<1.0	<1.0	<1.0
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >100	35	45	24
Chromium	ppm ASTM D5185m >20	1	2	<1
Nickel	ppm ASTM D5185m >4	0	<1	<1
Titanium	ppm ASTM D5185m	0	<1	0
Silver	ppm ASTM D5185m >3	<1	<1	1
Aluminum	ppm ASTM D5185m >20	5	6	7
Lead	ppm ASTM D5185m >40	4	6	5
Copper	ppm ASTM D5185m >330	2	3	4
Tin	ppm ASTM D5185m >15	<1	1	1
Vanadium	ppm ASTM D5185m	0	<1	0
Cadmium	ppm ASTM D5185m	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 250	4	7	7
Barium	ppm ASTM D5185m 10	0	0	0
Molybdenum	ppm ASTM D5185m 100	67	64	59
Manganese	ppm ASTM D5185m	1	1	<1
Magnesium	ppm ASTM D5185m 450	1065	1002	898
Calcium	ppm ASTM D5185m 3000	1213	1230	1137
Phosphorus	ppm ASTM D5185m 1150	1135	1070	928
Zinc	ppm ASTM D5185m 1350	1426	1380	1209
Sulfur	ppm ASTM D5185m 4250	3708	3491	3242

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >25	6	8	12
Sodium	ppm ASTM D5185m >216	2	3	2
Potassium	ppm ASTM D5185m >20	2	7	2

INFRA-RED



method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >3	1.5	▲ 3	1.9
Nitration	Abs/cm *ASTM D7624 >20	14.1	18.5	14.8
Sulfation	Abs/.1mm *ASTM D7415 >30	25.5	31.3	27.3

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	25.9	34.2	26.5
Base Number (BN)	mg KOH/g ASTM D2896 8.5	6.4	7.1	8.1







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	14.4	13.3	13.5	13.0

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0083844 **Received** : 15 Aug 2023
Lab Number : **05925334** **Diagnosed** : 16 Aug 2023
Unique Number : 10605281 **Diagnostician** : Angela Borella
Test Package : FLEET

GFL Environmental - 652 - Fredericksburg Hauling
 10954 Houser Drive
 Fredericksburg, VA
 US 22408
 Contact: WILLIAM MILO
 wmilo@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)