


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id **799449**

Component **Diesel Engine**

PETRO CANADA DURON SHP 10W30 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

QTS)		Aug2020	Jan 2021	Dec2022 Apr2023	Aug2023	
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0103076	PCA0095952	PCA0088086
Sample Date		Client Info		11 Aug 2023	05 Apr 2023	15 Dec 2022
Machine Age	mls	Client Info		0	0	370934
Oil Age	mls	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ΓΙΟΝ	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	_S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	28	13	23
Chromium	ppm	ASTM D5185m	>20	1	<1	1
Nickel	ppm	ASTM D5185m	>4	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	7	4	5
Lead	ppm	ASTM D5185m	>40	<1	0	0
Copper	ppm	ASTM D5185m	>330	7	4	6
Tin	ppm	ASTM D5185m	>15	<1	0	<1
Antimony	ppm	ASTM D5185m				
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	3	8	7
Barium	ppm	ASTM D5185m	0	0	1	0
Molybdenum	ppm	ASTM D5185m	50	61	63	79
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	950	884	875	916
Calcium	ppm	ASTM D5185m	1050	1114	1047	1237
Phosphorus	ppm	ASTM D5185m	995	938	942	966
Zinc	ppm	ASTM D5185m	1180	1224	1167	1259
Sulfur	ppm	ASTM D5185m	2600	3051	3097	3025
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6	6	5
Sodium	ppm	ASTM D5185m		5	4	4
Potassium	ppm	ASTM D5185m	>20	11	4	11
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.7	0.3	0.7
Nitration	Abs/cm	*ASTM D7624	>20	9.3	6.9	10.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.6	17.0	22.8
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.8	13.8	19.2
Base Number (BN)	mg KOH/g	ASTM D2896		6.7	7.5	5.9
,						



OIL ANALYSIS REPORT







Laboratory Sample No. Lab Number **Unique Number**

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : PCA0103076 : 05925762

: 10605709

Copper (ppm)

Viscosity @ 100°C

E 200

:St (100°C)

100

Received Diagnosed

Dec15/22

Dec15/22

: 16 Aug 2023 Diagnostician : Wes Davis

Apr5/23

Test Package : MOB 1 (Additional Tests: TBN) To discuss this sample report, contact Customer Service at 1-800-237-1369.

Jan 10/21

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

MILLER TRUCK LEASING #119

39 INDUSTRIAL AVE HASBROUCK HEIGHTS, NJ US 07604

Contact: MIKE LONGETTE mlongette@millertransgroup.com

T:

F: (201)528-7053

NONE

NONE

NONE

NONE

NONE

NONE

NORML

NORML

NEG

NEG

11.7

NONE

NONE

NONE

NONE

NONE

NONE

NORML

NORML

NEG

NEG

11.5

Silicon (ppm)

Base Number

Jan 10/21

E 40

20

KOH/g)

Aug11/23

: 16 Aug 2023

Dec15/22