


# OIL ANALYSIS REPORT

## Sample Rating Trend

**NORMAL**


Area  
**(94705X) Walgreens**  
Machine Id  
**[Walgreens] 136A62058**  
Component  
**Diesel Engine**  
Fluid  
**PETRO CANADA DURON SHP 10W30 (11 GAL)**

### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.

#### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

### SAMPLE INFORMATION

method	limit/base	current	history1	history2	
Sample Number	Client Info	<b>PCA0101016</b>	PCA0087918	PCA0076378	
Sample Date	Client Info	<b>26 Jul 2023</b>	23 Dec 2022	21 Jun 2022	
Machine Age	mls	Client Info	<b>537639</b>	479981	503105
Oil Age	mls	Client Info	<b>57658</b>	62723	39670
Oil Changed	Client Info	<b>Changed</b>	Changed	Changed	
Sample Status		<b>NORMAL</b>	NORMAL	NORMAL	

### CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >5	<b>&lt;1.0</b>	<1.0	<1.0
Glycol	WC Method	<b>NEG</b>	NEG	NEG

### WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >80	<b>43</b>	34	14
Chromium	ppm ASTM D5185m >5	<b>4</b>	4	2
Nickel	ppm ASTM D5185m >2	<b>0</b>	<1	<1
Titanium	ppm ASTM D5185m	<b>0</b>	0	<1
Silver	ppm ASTM D5185m >3	<b>0</b>	0	<1
Aluminum	ppm ASTM D5185m >30	<b>27</b>	25	10
Lead	ppm ASTM D5185m >30	<b>&lt;1</b>	<1	<1
Copper	ppm ASTM D5185m >150	<b>7</b>	5	4
Tin	ppm ASTM D5185m >5	<b>&lt;1</b>	<1	1
Vanadium	ppm ASTM D5185m	<b>&lt;1</b>	0	0
Cadmium	ppm ASTM D5185m	<b>0</b>	0	0

### ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 2	<b>1</b>	6	11
Barium	ppm ASTM D5185m 0	<b>0</b>	0	0
Molybdenum	ppm ASTM D5185m 50	<b>65</b>	58	56
Manganese	ppm ASTM D5185m 0	<b>&lt;1</b>	<1	<1
Magnesium	ppm ASTM D5185m 950	<b>953</b>	838	815
Calcium	ppm ASTM D5185m 1050	<b>1189</b>	1293	1288
Phosphorus	ppm ASTM D5185m 995	<b>970</b>	972	937
Zinc	ppm ASTM D5185m 1180	<b>1267</b>	1236	1220
Sulfur	ppm ASTM D5185m 2600	<b>3005</b>	2871	3183

### CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >20	<b>8</b>	8	5
Sodium	ppm ASTM D5185m	<b>4</b>	1	1
Potassium	ppm ASTM D5185m >20	<b>5</b>	2	0



### INFRA-RED

method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >3	<b>1.2</b>	1.4	0.8
Nitration	Abs/cm *ASTM D7624 >20	<b>10.6</b>	10.9	9.5
Sulfation	Abs/.1mm *ASTM D7415 >30	<b>23.3</b>	24.5	22.1

### FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	<b>18.6</b>	20.2	17.7
Base Number (BN)	mg KOH/g ASTM D2896	<b>5.6</b>	5.5	6.9





# OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.7	12.1

## GRAPHS



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : PCA0101016 **Received** : 16 Aug 2023  
**Lab Number** : 05925806 **Diagnosed** : 16 Aug 2023  
**Unique Number** : 10605753 **Diagnostician** : Wes Davis  
**Test Package** : FLEET

**Transervice - Shop 1373 - Berkeley-Anderson/Pendergrass**  
 101 Alliance Parkway  
 Willamston, SC  
 US 29697  
 Contact: Sonny Boucher  
 sboucher@transervice.com  
 T: (864)226-2304  
 F: (864)226-2329

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)