



PROBLEM SUMMARY

Sample Rating Trend


DIRT



Machine Id
420094
Component
2 Differential
Fluid
NOT GIVEN (--- GAL)



COMPONENT CONDITION SUMMARY



RECOMMENDATION

The oil change at the time of sampling has been noted. Resample at the next service interval to monitor. (Customer Sample Comment: 2nd Axle / Tag)

PROBLEMATIC TEST RESULTS

Sample Status				ABNORMAL	---	---
Silicon	ppm	ASTM D5185m	>285	▲ 339	---	---

Customer Id: GFL983
Sample No.: GFL0089398
Lab Number: 05928490
Test Package: FLEET



To manage this report scan the QR code

To discuss the diagnosis or test data:
Don Baldrige +1
don.b505@comcast.net

To change component or sample information:
Customer Service +1 1-800-237-1369
customerservice@wearcheck.com

RECOMMENDED ACTIONS

There are no recommended actions for this sample.


HISTORICAL DIAGNOSIS



OIL ANALYSIS REPORT

Sample Rating Trend

DIRT



Machine Id
420094
 Component
2 Differential
 Fluid
NOT GIVEN (--- GAL)

DIAGNOSIS

Recommendation

The oil change at the time of sampling has been noted. Resample at the next service interval to monitor. (Customer Sample Comment: 2nd Axle / Tag)

Wear

All component wear rates are normal.

Contamination

Elemental level of silicon (Si) above normal indicating ingress of seal material.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0089398	---	---
Sample Date	Client Info	15 Aug 2023	---	---
Machine Age	mls Client Info	109690	---	---
Oil Age	mls Client Info	109690	---	---
Oil Changed	Client Info	Changed	---	---
Sample Status		ABNORMAL	---	---

WEAR METALS

method	limit/base	current	history1	history2
Iron ppm	ASTM D5185m >870	375	---	---
Chromium ppm	ASTM D5185m >8	3	---	---
Nickel ppm	ASTM D5185m >25	13	---	---
Titanium ppm	ASTM D5185m >4	<1	---	---
Silver ppm	ASTM D5185m	0	---	---
Aluminum ppm	ASTM D5185m >40	17	---	---
Lead ppm	ASTM D5185m >25	0	---	---
Copper ppm	ASTM D5185m >60	1	---	---
Tin ppm	ASTM D5185m >5	0	---	---
Vanadium ppm	ASTM D5185m	0	---	---
Cadmium ppm	ASTM D5185m	0	---	---

ADDITIVES

method	limit/base	current	history1	history2
Boron ppm	ASTM D5185m	126	---	---
Barium ppm	ASTM D5185m	1	---	---
Molybdenum ppm	ASTM D5185m	0	---	---
Manganese ppm	ASTM D5185m	6	---	---
Magnesium ppm	ASTM D5185m	5	---	---
Calcium ppm	ASTM D5185m	65	---	---
Phosphorus ppm	ASTM D5185m	970	---	---
Zinc ppm	ASTM D5185m	29	---	---
Sulfur ppm	ASTM D5185m	22036	---	---

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon ppm	ASTM D5185m >285	▲ 339	---	---
Sodium ppm	ASTM D5185m	4	---	---
Potassium ppm	ASTM D5185m >20	2	---	---

VISUAL



method	limit/base	current	history1	history2
White Metal scalar	*Visual NONE	NONE	---	---
Yellow Metal scalar	*Visual NONE	NONE	---	---
Precipitate scalar	*Visual NONE	NONE	---	---
Silt scalar	*Visual NONE	NONE	---	---
Debris scalar	*Visual NONE	NONE	---	---
Sand/Dirt scalar	*Visual NONE	NONE	---	---
Appearance scalar	*Visual NORML	NORML	---	---
Odor scalar	*Visual NORML	NORML	---	---
Emulsified Water scalar	*Visual >.2	NEG	---	---
Free Water scalar	*Visual	NEG	---	---

FLUID PROPERTIES

method	limit/base	current	history1	history2
Visc @ 40°C cSt	ASTM D445	128	---	---






OIL ANALYSIS REPORT



SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				no image	no image
Bottom				no image	no image

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0089398
Lab Number : 05928490
Unique Number : 10608437
Test Package : FLEET

Received : 18 Aug 2023
Diagnosed : 21 Aug 2023
Diagnostician : Don Baldrige

GFL Environmental - 983 - Sugar Land Hauling
 16011 West Belfort Street
 Sugar Land, TX
 US 77498
 Contact: TECHNICIAN ACCOUNT
 wcgfldemo@gmail.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: