


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id **428035-402343**

Component

Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

GAL)		Apr2019	Sep2019 Apr2020	Jul2021 Nov2022	Aug2023	
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0079281	GFL0061276	GFL0051973
Sample Date		Client Info		11 Aug 2023	04 May 2023	17 Nov 2022
Machine Age	hrs	Client Info		10825	10144	9627
Oil Age	hrs	Client Info		681	517	700
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	ABNORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>110	20	55	84
Chromium	ppm	ASTM D5185m	>4	1	3	4
Nickel	ppm	ASTM D5185m	>2	0	<1	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>2	0	<1	0
Aluminum	ppm	ASTM D5185m	>25	5	5	3
Lead	ppm	ASTM D5185m	>45	0	<u>^</u> 28	1
Copper	ppm	ASTM D5185m	>85	0	<u>^</u> 298	2
Tin	ppm	ASTM D5185m	>4	0	5	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	2	2	2
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	85	77	56
Manganese	ppm	ASTM D5185m	0	0	4	<1
Magnesium	ppm	ASTM D5185m	1010	1304	1244	861
Calcium	ppm	ASTM D5185m	1070	1389	1401	1029
Phosphorus	ppm	ASTM D5185m	1150	1360	1268	935
Zinc	ppm	ASTM D5185m	1270	1844	1607	1159
Sulfur	ppm	ASTM D5185m	2060	5259	3387	2956
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>30	5	28	13
Sodium	ppm	ASTM D5185m		58	17	31
Potassium	ppm	ASTM D5185m	>20	0	4	2
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.7	0.5	2.5
Nitration	Abs/cm	*ASTM D7624	>20	10.4	12.8	14.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.9	25.3	27.0
FLUID DEGRADATION method limit/base current history1 history2						
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.0	25.7	23.6
Base Number (BN)	mg KOH/g	ASTM D2896		7.7	7.9	9.6
(Bi4)						



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPERTIES		method				history2	
Visc @ 100°C	cSt	ASTM D445	15.4	13.7	15.5	13.0	

GRAPHS













Certificate L2367

Laboratory Sample No. Lab Number **Unique Number** Test Package : FLEET

: GFL0079281 : 05929263 : 10609210

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received Diagnosed

: 21 Aug 2023 : 22 Aug 2023 Diagnostician : Don Baldridge GFL Environmental - 822 - Springfield Hauling

2120 West Bennett Street Springfield, MO US 65807

Contact: Dennis Moore dennis.moore@gflenv.com T: (417)403-3641

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)