


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id **26509**

Component **Diesel Engine**

PETRO CANADA DURON SHP 10W30 (34 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

4 ₀₀₀ 2018 Jan2019 Sep2019 Mey2020 Mer2021 Oct2021 Mer2023						
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0099762	PCA0093703	PCA0070822
Sample Date		Client Info		29 May 2023	20 Mar 2023	28 Apr 2022
Machine Age	mls	Client Info		0	426901	404583
Oil Age	mls	Client Info		20000	40000	20105
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATI	ON	method	limit/base	current	history1	history2
Fuel		WC Method	>6.0	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS	3	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	39	95	39
Chromium	ppm	ASTM D5185m	>20	<1	2	<1
Nickel	ppm	ASTM D5185m	>2	0	1	0
Titanium	ppm	ASTM D5185m		5	27	30
Silver	ppm	ASTM D5185m	>2	0	<1	<1
Aluminum	ppm	ASTM D5185m	>25	7	19	9
Lead	ppm	ASTM D5185m	>40	2	5	1
Copper	ppm	ASTM D5185m	>330	6	25	7
Tin	ppm	ASTM D5185m	>15	<1	2	<1
Antimony	ppm	ASTM D5185m				
Vanadium	ppm	ASTM D5185m		0	<1	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	0	5	20
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	50	57	41	35
Manganese	ppm	ASTM D5185m	0	<1	2	<1
Magnesium	ppm	ASTM D5185m	950	882	737	679
Calcium	ppm	ASTM D5185m	1050	1171	1321	1339
Phosphorus	ppm	ASTM D5185m	995	994	935	962
Zinc	ppm	ASTM D5185m	1180	1206	1202	1229
Sulfur	ppm	ASTM D5185m	2600	2967	3621	3065
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6	12	7
Sodium	ppm	ASTM D5185m		13	19	7
Potassium	ppm	ASTM D5185m	>20	6	17	8
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.6	1	0.5
Nitration	Abs/cm	*ASTM D7624	>20	10.7	12.2	10.6
Sulfation	Abs/.1mm	*ASTM D7415		20.7	25.9	22.2
FLUID DEGRAD	ATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.1	20.4	17.4
Base Number (BN)	mg KOH/g	ASTM D2896	-	6.7	4.2	6.7
Dase Mulliber (DIM)						




OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPE	RHES	method	iimit/base		nistory i	nistory2
Visc @ 100°C	cSt	ASTM D445	12.00	11.3	11.2	11.2

GRAPHS













Certificate L2367

Laboratory

Sample No. Lab Number **Unique Number** Test Package : FLEET

: PCA0099762 : 05930710

: 10615981

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 22 Aug 2023

Diagnosed : 22 Aug 2023 Diagnostician : Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

PERDUE FARMS - GEORGETOWN

20621 SAVANAH RD GEORGETOWN, DE

US 19947

Contact: ROBERT LOCKWOOD Robert.Lockwood@Perdue.com

> T: F:

Contact/Location: ROBERT LOCKWOOD - PERGEODE