

OIL ANALYSIS REPORT

Sample Rating Trend





Front Axle

Elui

CHEVRON RPM SYNTHETIC GEAR 75W90 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2		
Sample Number		Client Info		PCA0102269	PCA0092568	PCA0092500		
Sample Date		Client Info		17 Aug 2023	03 Apr 2023	27 Mar 2023		
Machine Age	mls	Client Info		151212	126652	125751		
Oil Age	mls	Client Info		151212	125751	125751		
Oil Changed		Client Info		Changed	Not Changd	N/A		
Sample Status				NORMAL	NORMAL	ABNORMAL		
WEAR METAL	S	method	limit/base	current	history1	history2		
Iron	ppm	ASTM D5185m	>500	122	100	93		
Chromium	ppm	ASTM D5185m	>10	<1	<1	0		
Nickel	ppm	ASTM D5185m	>10	0	0	0		
Titanium	ppm	ASTM D5185m		0	<1	0		
Silver	ppm	ASTM D5185m		0	0	0		
Aluminum	ppm	ASTM D5185m	>25	<1	1	3		
Lead	ppm	ASTM D5185m	>25	0	0	0		
Copper	ppm	ASTM D5185m	>50	41	24	24		
Tin	ppm	ASTM D5185m	>10	<1	<1	<1		
Vanadium	ppm	ASTM D5185m		<1	0	0		
Cadmium	ppm	ASTM D5185m		0	0	0		
ADDITIVES		method	limit/base	current	history1	history2		
Boron	ppm	ASTM D5185m		251	245	216		
Barium	ppm	ASTM D5185m		0	0	0		
Molybdenum	ppm	ASTM D5185m		19	19	19		
Manganese	ppm	ASTM D5185m		8	6	7		
Magnesium	ppm	ASTM D5185m		98	92	102		
Calcium	ppm	ASTM D5185m		205	193	193		
Phosphorus	ppm	ASTM D5185m		1340	1273	1293		
Zinc	ppm	ASTM D5185m		160	161	169		
Sulfur	ppm	ASTM D5185m		24953	19958	24699		
CONTAMINAN	TS	method	limit/base	current	history1	history2		
Silicon	ppm	ASTM D5185m	>75	40	34	35		
Sodium	ppm	ASTM D5185m		3	2	1		
Potassium	ppm	ASTM D5185m	>20	0	2	<1		
VISUAL		method	limit/base	current	history1	history2		
White Metal	scalar	*Visual	NONE	NONE	MODER	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE	NONE	🔺 MODER		
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG		
Free Water	scalar	*Visual		NEG	NEG	NEG		
FLUID PROPE	RTIES	method	limit/base	current	history1	history2		
Visc @ 40°C	cSt	ASTM D445	110	79.9	81.3	80.4		
3:22:40) Rev: 1						Submitted By: Paul Riddick		



OIL ANALYSIS REPORT

SAMPLE IMAGES



			,	,
	Color	no image	no image	no image
Juni 14/22 0ct28/22 Apr3/23 Aug 17/23	Bottom	no image	no image	no image
	GRAPHS			
	Ferrous Alloys			
	180 160 140 120			
	180 170 160 150			
554 140-151	140 - Abnormal			
	100-			
	90			
	70			
	Sep16/21 Feb10/22 Jun14/22 Oct28/22 Aug17/23 Aug17/23			
	: WearCheck USA - 501 Madison Ave., Cary, NC 2751 : PCA0102269 Received : 25 Aug 2023 : 05935032 Diagnosed : 28 Aug 2023 : 10620303 Diagnostician : Sean Felton : FLEET contact Customer Service at 1-800-237-1369.		Contact: GEOR	IDENCE BLVD OLUMBIA, SC US 29210 GE EDWARDS @nwwhite.com
	re outside of the ISO 17025 scope of accreditation. ifications are based on the simple acceptance decision rule	(JCGM 106:2012)	T: F: