


OIL ANALYSIS REPORT

Sample Rating Trend









Machine Id 913028 Component Diesel Engine Fluid

PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

)N SHP 15W40 (- GAL)	Nov202	2 Jan 2023	Jun2023 Au	g2023	
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0091491	GFL0082819	GFL0063314
Sample Date		Client Info		22 Aug 2023	06 Jun 2023	04 Jan 2023
Machine Age	hrs	Client Info		2909	2307	1126
Oil Age	hrs	Client Info		600	600	600
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>120	22	52	14
Chromium	ppm	ASTM D5185m	>20	<1	2	<1
Nickel	ppm	ASTM D5185m	>5	2	8	4
Titanium	ppm	ASTM D5185m	>2	0	0	0
Silver	ppm	ASTM D5185m	>2	<1	0	<1
Aluminum	ppm	ASTM D5185m	>20	3	0	1
Lead	ppm	ASTM D5185m	>40	0	<1	1
Copper	ppm	ASTM D5185m	>330	6	24	56
Tin	ppm	ASTM D5185m	>15	1	2	1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	2	2	6
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	63	62	56
Manganese	ppm	ASTM D5185m	0	<1	1	<1
Magnesium	ppm	ASTM D5185m	1010	1015	925	861
Calcium	ppm	ASTM D5185m	1070	1156	1116	1160
Phosphorus	ppm	ASTM D5185m	1150	1081	985	975
Zinc	ppm	ASTM D5185m	1270	1345	1240	1231
Sulfur	ppm	ASTM D5185m	2060	3520	2346	3354
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	4	6	3
Sodium	ppm	ASTM D5185m		4	3	3
Potassium	ppm	ASTM D5185m	>20	0	2	<1
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>4	0.7	1.1	0.3
Nitration	Abs/cm	*ASTM D7624	>20	9.1	12.4	7.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.1	25.5	19.7
FLUID DEGRA	OATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.8	23.2	15.2
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	6.9	4.2	7.9
()	0 - 0					



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPE	RHES	method				history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.8	13.8	13.3

GRAPHS













Certificate L2367

Laboratory Sample No. Lab Number Test Package : FLEET

: GFL0091491 : 05935271 Unique Number : 10620542

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received : 25 Aug 2023 Diagnosed : 28 Aug 2023 Diagnostician : Wes Davis

GFL Environmental - 465 - Pontiac

888 Baldwin Pontiac, MI US 48340

Contact: Ricky Matthews rickymathews@gflenv.com T: (586)825-9514

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)