

OIL ANALYSIS REPORT

Sample Rating Trend







KEMP QUARRIES / PRYOR STONE [65097] Machine Id WL137

Component Rear Right Final Drive

Fluid

PETRO CANADA PRODURO TO-4 SAE 50 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment: Pm4 performed. All oil samples taken. All oils, and all filters changed.)

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil

Fluid Condition


The condition of the oil is acceptable for the time in service

RO TO-4 SAE 50 (-	GAL)	Apr2020 Ju	2021 Nov2021 Apr2022	Jul2022 Oct2022 Feb2023 May20	23 Jul2023	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0084231	PCA0083973	PCA0086203
Sample Date		Client Info		28 Jul 2023	18 May 2023	23 Feb 2023
Machine Age	hrs	Client Info		31785	31319	30765
Oil Age	hrs	Client Info		2146	1680	1126
Oil Changed		Client Info		Changed	Oil Added	Oil Added
Sample Status				NORMAL	NORMAL	NORMAL
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>800	9	9	8
Chromium	ppm	ASTM D5185m	>10	<1	<1	<1
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m	>15	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>75	4	2	1
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>75	1	<1	1
Tin	ppm	ASTM D5185m	>8	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	0	0	2
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	0	1	1
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	9	15	21	21
Calcium	ppm	ASTM D5185m	3114	3474	3435	3343
Phosphorus	ppm	ASTM D5185m	1099	996	970	927
Zinc	ppm	ASTM D5185m	1245	1218	1188	1146
Sulfur	ppm	ASTM D5185m	7086	7699	7570	7547
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>400	14	16	17
Sodium	ppm	ASTM D5185m		<1	1	<1
Potassium	ppm	ASTM D5185m	>20	0	<1	0
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	213.9	190	189	190



OIL ANALYSIS REPORT







Certificate L2367

Laboratory Sample No. Lab Number **Unique Number**

: PCA0084231 : 05935696 : 10620967 Test Package : MOB 1

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 25 Aug 2023 : 28 Aug 2023 Diagnosed Diagnostician : Don Baldridge

Kemp Quarries - Pryor Stone - Pryor 1050 E 520 Rd Pryor, OK US 74361 Contact: pryor@pryorstone.com

no image

no image

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: