

# **OIL ANALYSIS REPORT**

## Sample Rating Trend

# **NORMAL**



# KEMP QUARRIES / PRYOR STONE [65253] **OHT078**

Component **Rear Left Final Drive** 

PETRO CANADA PRODURO TO-4 SAE 50 (





### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor. ( Customer Sample Comment: Pm2 performed. All oil samples taken. Engine oil, transmission oil, and all filters changed, )

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the


#### **Fluid Condition**

The condition of the oil is acceptable for the time in service.

RO TO-4 SAE 50 ( GAL)						
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0084245	PCA0083998	PCA0070558
Sample Date		Client Info		11 Aug 2023	22 May 2023	17 Feb 2023
Machine Age	hrs	Client Info		34182	33716	33140
Oil Age	hrs	Client Info		1042	576	1976
Oil Changed		Client Info		Oil Added	Oil Added	Changed
Sample Status				NORMAL	NORMAL	NORMAL
WEAR META	LS	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>800	104	37	96
Chromium	ppm	ASTM D5185m	>10	<1	<1	<1
Nickel	ppm	ASTM D5185m	>5	0	<1	<1
Titanium	ppm	ASTM D5185m	>15	<1	<1	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>75	4	2	2
Lead	ppm	ASTM D5185m	>10	<1	<1	2
Copper	ppm	ASTM D5185m		8	4	10
Tin	ppm	ASTM D5185m	>8	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	0	0	<1
Barium	ppm	ASTM D5185m	0	0	2	0
Molybdenum	ppm	ASTM D5185m	0	0	<1	<1
Manganese	ppm	ASTM D5185m		1	<1	<1
Magnesium	ppm	ASTM D5185m	9	18	15	16
Calcium	ppm	ASTM D5185m		3221	3233	2448
Phosphorus	ppm	ASTM D5185m	1099	986	981	860
Zinc	ppm	ASTM D5185m	1245	1225	1204	1048
Sulfur	ppm	ASTM D5185m	7086	4767	4294	5217
CONTAMINAL	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>400	18	17	9
Sodium	ppm	ASTM D5185m		2	0	2
Potassium	ppm	ASTM D5185m	>20	0	1	<1
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	MODER	MODER
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	MODER	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPI	ERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	213.9	159	172	159
-FO-FO\ D4						0 1 ' 1 5



# **OIL ANALYSIS REPORT**





# **GRAPHS** Iron (ppm) Lead (ppm) 1400 25 1200 20 1000 800 E 15 600 400 200 Chromium (ppm) Aluminum (ppm) 25 20 E 15 Silicon (ppm) Copper (ppm) 100 150 600 틆 100 50 Viscosity @ 40°C Additives 3000 240 2500 220 00 200 2000 1500 1000 160 500 140



Certificate L2367

Laboratory Sample No. Lab Number **Unique Number** 

: 05935704

: PCA0084245 : 10620975 Test Package : MOB 1

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 25 Aug 2023

: 28 Aug 2023 Diagnosed Diagnostician : Don Baldridge

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Kemp Quarries - Pryor Stone - Pryor

1050 E 520 Rd Pryor, OK US 74361

Contact: pryor@pryorstone.com

T:

F: