

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id 922039-282 Component Diesel Engine

Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- LTR)

DIAGNOSIS Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

N 3HP 13W4U (-	30P 13W40 (LIK)			Jun2023 Aug20		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0066131	GFL0066129	GFL0055743
Sample Date		Client Info		18 Aug 2023	20 Jun 2023	06 Oct 2022
Machine Age	hrs	Client Info		7585	7098	94795
Oil Age	hrs	Client Info		600	500	0
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>120	43	25	17
Chromium	ppm	ASTM D5185m	>20	1	1	1
Nickel	ppm	ASTM D5185m	>5	<1	<1	<1
Titanium	ppm	ASTM D5185m	>2	<1	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	2	3	3
Lead	ppm	ASTM D5185m	>40	1	<1	<1
Copper	ppm	ASTM D5185m	>330	3	2	5
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		<1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	3	7	12
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	47	68	54
Manganese	ppm	ASTM D5185m	0	1	<1	<1
Magnesium	ppm	ASTM D5185m	1010	736	1032	838
Calcium	ppm	ASTM D5185m	1070	1054	1168	1168
Phosphorus	ppm	ASTM D5185m	1150	802	1050	896
Zinc	ppm	ASTM D5185m	1270	1018	1369	1133
Sulfur	ppm	ASTM D5185m	2060	2655	3303	2964
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5	5	8
Sodium	ppm	ASTM D5185m		9	10	6
Potassium	ppm	ASTM D5185m	>20	4	3	2
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>4	0.7	1.1	0.7
Nitration	Abs/cm	*ASTM D7624	>20	8.5	11.8	9.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.4	26.0	22.7
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.6	22.7	18.9
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.6	6.1	7.3
. ,						



OIL ANALYSIS REPORT



VISUAL		method				history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


14.1

14.9

14.0


18 - Abnormal		
0	 	
016		
Base 00 15 15	 	
₹3 14 · · · · · · · · · · · · · · · · · ·	 	
13 Abnormal		
12-	 	
11	m	
Oct6/2;	20/2:	
ŏ	ZII	


Visc @ 100°C **GRAPHS**




cSt

ASTM D445 15.4











Laboratory Sample No.

Lab Number Unique Number : 10622197

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0066131 : 05936926

Received Diagnosed Diagnostician : Wes Davis

: 29 Aug 2023 : 29 Aug 2023

GFL Environmental - 904A - Thorpe

N14985 Tieman Ave Thorp, WI US 54771 Contact: Andy Kane akane@gflenv.com T: (715)202-3420

Test Package : FLEET Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)