


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
VOLVO 26605 (S/N 4V4WC9EJ3JN899062)

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 10W30 (40 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PCA0099311	PCA0093684	PCA0085262
Sample Date	Client Info		24 Aug 2023	04 May 2023	02 Feb 2023
Machine Age	mls	Client Info	261137	245098	229173
Oil Age	mls	Client Info	32831	15925	44653
Oil Changed	Client Info		Changed	Not Changd	Changed
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>6.0	<1.0	<1.0	<1.0
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >100	53	33	84
Chromium	ppm	ASTM D5185m >20	<1	<1	1
Nickel	ppm	ASTM D5185m >2	<1	2	2
Titanium	ppm	ASTM D5185m	0	<1	0
Silver	ppm	ASTM D5185m >2	<1	<1	0
Aluminum	ppm	ASTM D5185m >25	5	7	5
Lead	ppm	ASTM D5185m >40	3	3	9
Copper	ppm	ASTM D5185m >330	11	8	22
Tin	ppm	ASTM D5185m >15	<1	2	2
Vanadium	ppm	ASTM D5185m	0	<1	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 2	1	4	0
Barium	ppm	ASTM D5185m 0	0	0	0
Molybdenum	ppm	ASTM D5185m 50	58	60	66
Manganese	ppm	ASTM D5185m 0	<1	1	1
Magnesium	ppm	ASTM D5185m 950	960	993	953
Calcium	ppm	ASTM D5185m 1050	1119	1101	1187
Phosphorus	ppm	ASTM D5185m 995	934	1051	1004
Zinc	ppm	ASTM D5185m 1180	1250	1317	1301
Sulfur	ppm	ASTM D5185m 2600	3082	3619	2468

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	7	11	10
Sodium	ppm	ASTM D5185m	14	11	23
Potassium	ppm	ASTM D5185m >20	4	5	10



INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.7	0.4	0.9
Nitration	Abs/cm	*ASTM D7624 >20	10.3	9.4	11.6
Sulfation	Abs/.1mm	*ASTM D7415 >30	23.3	19.7	24.6

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	19.9	16.0	21.4
Base Number (BN)	mg KOH/g	ASTM D2896	5.2	7.5	4.1





OIL ANALYSIS REPORT



PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.2	11.1

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0099311 **Received** : 07 Sep 2023
Lab Number : 05944471 **Diagnosed** : 08 Sep 2023
Unique Number : 10635083 **Diagnostician** : Wes Davis
Test Package : FLEET

PERDUE FARMS - ACCOMAC
 22520 LANKFORD HWY
 ACCOMAC, VA
 US 23301
 Contact: PEGGY KIMES
 peggy.kimes@perdue.com
 T: (757)787-5304
 F: (757)787-5208

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)