OIL ANALYSIS REPORT

OIL DIAGNOSTICS

Sample Rating Trend

VISCOSITY

Area
G.LOPES CONSTRUCTION INC./OFF-ROAD
Machine Id
L-96
Component
Rear Differential
Fluid
PETRO CANADA TRAXON 80W90 (--- GAL)

DIAGNOSIS

▲ Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

▲ Fluid Condition

The oil viscosity is lower than normal. Additive levels indicate the addition of a different brand, or type of oil. Confirm oil type. The AN level is acceptable for this fluid.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**PCA0104554**	---	---
Sample Date		Client Info		**05 Sep 2023**	---	---
Machine Age	hrs	Client Info		**5682**	---	---
Oil Age	hrs	Client Info		**5682**	---	---
Oil Changed		Client Info		**N/A**	---	---
Sample Status				**ATTENTION**	---	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	**267**	---	---
Chromium	ppm	ASTM D5185m	>3	**1**	---	---
Nickel	ppm	ASTM D5185m	>3	**<1**	---	---
Titanium	ppm	ASTM D5185m	>2	**<1**	---	---
Silver	ppm	ASTM D5185m	>2	**0**	---	---
Aluminum	ppm	ASTM D5185m	>30	**4**	---	---
Lead	ppm	ASTM D5185m	>13	**0**	---	---
Copper	ppm	ASTM D5185m	>103	**24**	---	---
Tin	ppm	ASTM D5185m	>5	**0**	---	---
Vanadium	ppm	ASTM D5185m		**0**	---	---
Cadmium	ppm	ASTM D5185m		**0**	---	---

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	243	▲ **0**	---	---
Barium	ppm	ASTM D5185m	1	**3**	---	---
Molybdenum	ppm	ASTM D5185m		**0**	---	---
Manganese	ppm	ASTM D5185m		**3**	---	---
Magnesium	ppm	ASTM D5185m	2	**9**	---	---
Calcium	ppm	ASTM D5185m	6	▲ **3003**	---	---
Phosphorus	ppm	ASTM D5185m	987	**1071**	---	---
Zinc	ppm	ASTM D5185m	1	▲ **1247**	---	---
Sulfur	ppm	ASTM D5185m	21530	▲ **5839**	---	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>100	**6**	---	---
Sodium	ppm	ASTM D5185m		**<1**	---	---
Potassium	ppm	ASTM D5185m	>20	**1**	---	---

FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	1.9	**0.94**	---	---

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	---	---
Yellow Metal	scalar	*Visual	NONE	**NONE**	---	---
Precipitate	scalar	*Visual	NONE	**NONE**	---	---
Silt	scalar	*Visual	NONE	**NONE**	---	---
Debris	scalar	*Visual	NONE	**NONE**	---	---
Sand/Dirt	scalar	*Visual	NONE	**NONE**	---	---
Appearance	scalar	*Visual	NORML	**NORML**	---	---
Odor	scalar	*Visual	NORML	**NORML**	---	---
Emulsified Water	scalar	*Visual	>.2	**NEG**	---	---
Free Water	scalar	*Visual		**NEG**	---	---

OIL ANALYSIS REPORT

OIL DIAGNOSTICS

Additives



Additives



Acid Number



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	141.0	▲ **96.9**	---	---

SAMPLE IMAGES				current	history1	history2
Color				*no image*	*no image*	*no image*
Bottom				*no image*	*no image*	*no image*

GRAPHS

Iron (ppm)



Lead (ppm)



Aluminum (ppm)



Chromium (ppm)



Copper (ppm)



Silicon (ppm)



Viscosity @ 40°C



Acid Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0104554
Lab Number : 05944732
Unique Number : 10635344
Test Package : MOB 2

Received : 07 Sep 2023
Diagnosed : 10 Sep 2023
Diagnostician : Don Baldridge

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

G LOPES CONSTRUCTION
565 WINTHROP ST
TAUNTON, MA
US 02780
Contact: BUTCH MCGRATH
bmcgrath@glopes.com
T:
F:

Report Id: GLOTAU [WUSCAR] 05944732 (Generated: 09/11/2023 08:55:16) Rev: 1

Submitted By: MATT MANOLI