


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
Active
Machine Id
47
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (10 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PCA0098316	PCA0078252	PCA0022873
Sample Date	Client Info		05 Sep 2023	25 Oct 2022	08 Sep 2020
Machine Age	hrs	Client Info	1876549	1876549	21750
Oil Age	hrs	Client Info	1876549	1876549	0
Oil Changed	Client Info		N/A	N/A	N/A
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	<1.0	<1.0
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >100	32	34	43
Chromium	ppm	ASTM D5185m >20	2	3	4
Nickel	ppm	ASTM D5185m >4	<1	0	0
Titanium	ppm	ASTM D5185m	<1	<1	<1
Silver	ppm	ASTM D5185m >3	0	0	<1
Aluminum	ppm	ASTM D5185m >20	2	1	1
Lead	ppm	ASTM D5185m >40	20	20	12
Copper	ppm	ASTM D5185m >330	104	<1	1
Tin	ppm	ASTM D5185m >15	<1	<1	1
Antimony	ppm	ASTM D5185m	---	---	<1
Vanadium	ppm	ASTM D5185m	0	<1	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	8	0	8
Barium	ppm	ASTM D5185m 0	2	0	0
Molybdenum	ppm	ASTM D5185m 60	63	56	62
Manganese	ppm	ASTM D5185m 0	<1	<1	<1
Magnesium	ppm	ASTM D5185m 1010	955	966	949
Calcium	ppm	ASTM D5185m 1070	1122	1133	1154
Phosphorus	ppm	ASTM D5185m 1150	1032	981	990
Zinc	ppm	ASTM D5185m 1270	1256	1290	1294
Sulfur	ppm	ASTM D5185m 2060	2943	3279	2364

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	4	4	3
Sodium	ppm	ASTM D5185m	4	5	19
Potassium	ppm	ASTM D5185m >20	5	10	28



INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.5	1.4	2.6
Nitration	Abs/cm	*ASTM D7624 >20	9.4	11.9	11.5
Sulfation	Abs/.1mm	*ASTM D7415 >30	22.2	25.3	26.3

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	18.9	20.8	19.1
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	8.66	7.45	8.72









OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	13.3	14.2	14.7

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0098316 **Received** : 07 Sep 2023
Lab Number : **05944755** **Diagnosed** : 08 Sep 2023
Unique Number : 10635367 **Diagnostician** : Wes Davis
Test Package : MOB 2

REDI MIX SERVICES
 120 BERKLEY ST
 TAUNTON, MA
 US 02780
 Contact: HENRY HOLLER
 hholler@glopes.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: