

OIL ANALYSIS REPORT



Machine Id 130130

Component Diesel Engine

PETRO CANADA DURON SHP 10W30 (--- QTS)

DIAGNOSIS

Recommendation

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

Elui

Metal levels are typical for a new component breaking in.

Contamination

Elemental level of silicon (Si) above normal indicating ingress of seal material.


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.


SAMPLE INFORMA	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0100940		
Sample Date		Client Info		21 Aug 2023		
	mls	Client Info		10273		
Ű	mls	Client Info		0		
Oil Changed		Client Info		Changed		
Sample Status				ABNORMAL		
CONTAMINATIC	N	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Glycol		WC Method		NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron p	ppm	ASTM D5185m	>100	72		
Chromium p	ppm	ASTM D5185m	>20	1		
	ppm	ASTM D5185m	>4	<1		
	ppm	ASTM D5185m		<1		
	ppm	ASTM D5185m	>3	<1		
	ppm	ASTM D5185m	>20	18		
	ppm	ASTM D5185m	>40	4		
-	ppm	ASTM D5185m	>330	66		
	ppm	ASTM D5185m	>15	5		
	ppm	ASTM D5185m		<1		
- · · ·	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron p	ppm	ASTM D5185m	2	153		
Barium p	ppm	ASTM D5185m	0	6		
Molybdenum p	ppm	ASTM D5185m	50	8		
Manganese p	ppm	ASTM D5185m	0	4		
Magnesium p	ppm	ASTM D5185m	950	16		
Calcium p	ppm	ASTM D5185m	1050	1183		
Phosphorus p	ppm	ASTM D5185m				
		AGTIVI DJ TOJITI	995	882		
Zinc p	ppm	ASTM D5185m	995 1180	882 1154		
	ppm ppm	ASTM D5185m	1180	1154		
Sulfur p	ppm ppm	ASTM D5185m ASTM D5185m method	1180 2600	1154 3711		
Sulfur p CONTAMINANT Silicon p	ppm ppm S	ASTM D5185m ASTM D5185m method	1180 2600 limit/base	1154 3711 current	 history1	 history2
Sulfur p CONTAMINANT Silicon p Sodium p	opm opm S opm	ASTM D5185m ASTM D5185m Method ASTM D5185m ASTM D5185m	1180 2600 limit/base	1154 3711 current ▲ 54	 history1	 history2
Sulfur p CONTAMINANT Silicon p Sodium p	ppm ppm S ppm ppm	ASTM D5185m ASTM D5185m Method ASTM D5185m ASTM D5185m	1180 2600 limit/base >25	1154 3711 current ▲ 54 3	 history1 	 history2
Sulfur p CONTAMINANTS Silicon p Sodium p Potassium p INFRA-RED	ppm ppm S ppm ppm	ASTM D5185m ASTM D5185m Method ASTM D5185m ASTM D5185m ASTM D5185m	1180 2600 limit/base >25 >20	1154 3711 current ▲ 54 3 6	 history1 	 history2
Sulfur p CONTAMINANTS Silicon p Sodium p Potassium p INFRA-RED Soot % 9	ppm ppm S ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m method *ASTM D7844	1180 2600 limit/base >25 >20 limit/base >3	1154 3711 current ▲ 54 3 6 current	 history1 history1	history2
Sulfur p CONTAMINANTS Silicon p Sodium p Potassium p INFRA-RED Soot % 9 Nitration A	ppm ppm S ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m *ASTM D7844 *ASTM D7824	1180 2600 limit/base >25 >20 limit/base >3	1154 3711 <u>current</u> ▲ 54 3 6 <u>current</u> 0.4	 history1 history1 	history2 history2 history2
Sulfur p CONTAMINANTS Silicon p Sodium p Potassium p INFRA-RED Soot % 9 Nitration A	ppm ppm S ppm ppm ppm ppm % Abs/cm Abs/.1mm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m *ASTM D7844 *ASTM D7624	1180 2600 limit/base >25 >20 limit/base >3 >20	1154 3711 current ▲ 54 3 6 current 0.4 7.8	 history1 history1 history1	 history2 history2 history2
Sulfur p CONTAMINANTS Silicon p Sodium p Potassium p INFRA-RED Soot % 9 Nitration A Sulfation A	ppm ppm S ppm ppm ppm ppm % Abs/cm Abs/.1mm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m *ASTM D7844 *ASTM D7624	1180 2600 limit/base >25 >20 limit/base >3 >20 >30 limit/base	1154 3711 current ▲ 54 3 6 current 0.4 7.8 20.9	 history1 history1 	 history2 history2 history2




OIL ANALYSIS REPORT









Laboratory

Sample No.

Lab Number