




# OIL ANALYSIS REPORT

Sample Rating Trend

**NORMAL**



Machine Id  
**413017**  
Component  
**Diesel Engine**  
Fluid  
**PETRO CANADA DURON SHP 15W40 (--- QTS)**



## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

Metal levels are typical for a new component breaking in.

### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>GFL0069206</b>	GFL0069152	GFL0069165
Sample Date	Client Info		<b>07 Sep 2023</b>	24 Aug 2023	03 Aug 2023
Machine Age	hrs	Client Info	<b>1447</b>	1340	1195
Oil Age	hrs	Client Info	<b>107</b>	553	408
Oil Changed	Client Info		<b>Not Chngd</b>	Changed	Not Chngd
Sample Status			<b>NORMAL</b>	NORMAL	NORMAL

## CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<b>&lt;1.0</b>	<1.0	<1.0
Glycol	WC Method		<b>NEG</b>	NEG	NEG

## WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >120	<b>4</b>	15	11
Chromium	ppm	ASTM D5185m >20	<b>&lt;1</b>	<1	<1
Nickel	ppm	ASTM D5185m >5	<b>&lt;1</b>	1	1
Titanium	ppm	ASTM D5185m >2	<b>0</b>	0	<1
Silver	ppm	ASTM D5185m >2	<b>&lt;1</b>	<1	1
Aluminum	ppm	ASTM D5185m >20	<b>2</b>	9	6
Lead	ppm	ASTM D5185m >40	<b>&lt;1</b>	0	0
Copper	ppm	ASTM D5185m >330	<b>9</b>	58	24
Tin	ppm	ASTM D5185m >15	<b>&lt;1</b>	1	<1
Vanadium	ppm	ASTM D5185m	<b>0</b>	0	0
Cadmium	ppm	ASTM D5185m	<b>0</b>	0	0

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	<b>5</b>	5	5
Barium	ppm	ASTM D5185m 0	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m 60	<b>58</b>	64	64
Manganese	ppm	ASTM D5185m 0	<b>1</b>	<1	<1
Magnesium	ppm	ASTM D5185m 1010	<b>989</b>	933	841
Calcium	ppm	ASTM D5185m 1070	<b>1061</b>	1140	1124
Phosphorus	ppm	ASTM D5185m 1150	<b>1047</b>	1023	974
Zinc	ppm	ASTM D5185m 1270	<b>1324</b>	1291	1170
Sulfur	ppm	ASTM D5185m 2060	<b>3968</b>	3410	2711

## CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	<b>4</b>	6	6
Sodium	ppm	ASTM D5185m	<b>3</b>	4	0
Potassium	ppm	ASTM D5185m >20	<b>6</b>	26	23

## INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >4	<b>0.1</b>	0.4	0.3
Nitration	Abs/cm	*ASTM D7624 >20	<b>5.0</b>	7.8	7.1
Sulfation	Abs/.1mm	*ASTM D7415 >30	<b>17.2</b>	19.4	18.7

## FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	<b>12.9</b>	15.5	14.7
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	<b>8.4</b>	7.1	7.5








# OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	<b>13.5</b>	13.0	13.3

## GRAPHS



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0069206 **Received** : 11 Sep 2023  
**Lab Number** : **05947009** **Diagnosed** : 12 Sep 2023  
**Unique Number** : 10642968 **Diagnostician** : Wes Davis  
**Test Package** : FLEET

**GFL Environmental - 073 - Warner Robins - Transwaste**  
 155 Story Road  
 Warner Robins, GA  
 US 31093  
 Contact: JOSH MALONEY  
 jmaloney@gflenv.com  
 T:  
 F:

Certificate L2367  
 To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)