OIL DIAGNOSTICS

OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Machine Id
T311
Component
Rear Differential
Fluid
GEAR OIL SAE 75W90 (--- GAL)

DIAGNOSIS

Recommendation
Resample at the next service interval to monitor.

Wear
All component wear rates are normal.

Contamination
There is no indication of any contamination in the oil.

Fluid Condition
The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**PCA0104163**	PCA0095696	PCA0085019
Sample Date		Client Info		**06 Sep 2023**	27 Apr 2023	30 Nov 2022
Machine Age	hrs	Client Info		**7852**	5179	5179
Oil Age	hrs	Client Info		**7852**	5179	5179
Oil Changed		Client Info		**Changed**	Not Changd	Not Changd
Sample Status				**NORMAL**	ABNORMAL	NORMAL

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	**63**	50	35
Chromium	ppm	ASTM D5185m	>10	**<1**	<1	<1
Nickel	ppm	ASTM D5185m	>10	**0**	0	0
Titanium	ppm	ASTM D5185m		**0**	0	0
Silver	ppm	ASTM D5185m		**0**	0	0
Aluminum	ppm	ASTM D5185m	>25	**1**	1	<1
Lead	ppm	ASTM D5185m	>25	**0**	0	0
Copper	ppm	ASTM D5185m	>100	**0**	<1	<1
Tin	ppm	ASTM D5185m	>10	**0**	0	0
Vanadium	ppm	ASTM D5185m		**0**	0	0
Cadmium	ppm	ASTM D5185m		**0**	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	400	**227**	232	212
Barium	ppm	ASTM D5185m	200	**0**	0	0
Molybdenum	ppm	ASTM D5185m	12	**6**	7	8
Manganese	ppm	ASTM D5185m		**3**	2	2
Magnesium	ppm	ASTM D5185m	12	**97**	92	97
Calcium	ppm	ASTM D5185m	150	**192**	196	189
Phosphorus	ppm	ASTM D5185m	1650	**1291**	1292	1300
Zinc	ppm	ASTM D5185m	125	**133**	140	138
Sulfur	ppm	ASTM D5185m	22500	**24297**	24718	25056

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	**12**	7	6
Sodium	ppm	ASTM D5185m		**2**	2	1
Potassium	ppm	ASTM D5185m	>20	**<1**	<1	0

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	**NONE**	▲ MODER	VLITE
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	**NEG**	NEG	NEG
Free Water	scalar	*Visual		**NEG**	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	109	**85.2**	86.9	89.4

OIL ANALYSIS REPORT

Viscosity @ 40°C



SAMPLE IMAGES	method	limit/base	current	history1	history2
Color			no image	no image	no image
Bottom			no image	no image	no image

GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 40°C



Certificate L2367

Laboratory	: WearCheck USA - 501 Madison Ave., Cary, NC 27513		
Sample No.	: PCA0104163	**Received**	: 11 Sep 2023
Lab Number	: 05947610	**Diagnosed**	: 13 Sep 2023
Unique Number	: 10643569	**Diagnostician**	: Sean Felton
Test Package	: FLEET		

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

NW WHITE & CO - COLUMBIA DIVISION
100 INDEPENDENCE BLVD
COLUMBIA, SC
US 29210
Contact: Paul Riddick
PRiddick@nwwhite.com
T: (803)750-6062
F: