

OIL ANALYSIS REPORT

Sample Rating Trend







928030-1190

Component

Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0088268	GFL0077504	GFL0077521
Sample Date		Client Info		05 Sep 2023	21 Jul 2023	23 Jun 2023
Machine Age	hrs	Client Info		11709	11429	11277
Oil Age	hrs	Client Info		288	589	440
Oil Changed		Client Info		Changed	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>120	5	10	8
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>5	6	12	7
Titanium	ppm	ASTM D5185m	>2	0	<1	0
Silver	ppm	ASTM D5185m	>2	<1	<1	<1
Aluminum	ppm	ASTM D5185m	>20	8	6	3
Lead	ppm	ASTM D5185m	>40	0	0	0
Copper	ppm	ASTM D5185m	>330	0	2	<1
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	<1	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	4	1	43
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	58	64	59
Manganese	ppm	ASTM D5185m	0	<1	1	<1
Magnesium	ppm	ASTM D5185m	1010	871	985	948
Calcium	ppm	ASTM D5185m	1070	1018	1156	1051
Phosphorus	ppm	ASTM D5185m	1150	941	1031	1020
Zinc	ppm	ASTM D5185m	1270	1117	1232	1295
Sulfur	ppm	ASTM D5185m	2060	3333	3550	3767
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	4	5	5
Sodium	ppm	ASTM D5185m		3	5	3
Potassium	ppm	ASTM D5185m	>20	21	8	10
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>4	0.3	0.4	0.3
Nitration	Abs/cm	*ASTM D7624	>20	6.2	8.1	7.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.1	18.2	18.5
FLUID DEGRADATION method limit/base current history1 history2						
Oxidation	Abs/.1mm	*ASTM D7414	>25	12.7	14.4	14.4
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.5	8.0	8.6



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPE	KIIES	metnoa	ilmit/base	current	nistory i	nistory2
Visc @ 100°C	cSt	ASTM D445	15.4	12.9	13.3	13.4

GRAPHS













Certificate L2367

Laboratory Sample No. Lab Number Unique Number : 10643781 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0088268 : 05947822

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received : 12 Sep 2023 Diagnosed

: 13 Sep 2023 Diagnostician : Wes Davis

GFL Environmental - 625 - Harrison Hauling

4102 Industrial Pkwy Harrison, MI US 48625

Contact: RON TROJANEK

ront@northerna1.com T: (231)624-0372

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)