


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id **228077** Component

Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

āAL)		Jan202	3 Jun 2023	Jul2023 S	ep 2023		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2	
Sample Number		Client Info		GFL0086867	GFL0072553	GFL0068315	
Sample Date		Client Info		07 Sep 2023	12 Jul 2023	20 Jun 2023	
Machine Age	hrs	Client Info		23670	600	0	
Oil Age	hrs	Client Info		600	600	0	
Oil Changed		Client Info		Changed	Changed	N/A	
Sample Status				NORMAL	NORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2	
Fuel		WC Method	>5	<1.0	<1.0	<1.0	
Glycol		WC Method		NEG	NEG	NEG	
WEAR METAL	.S	method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m	>100	6	17	10	
Chromium	ppm	ASTM D5185m	>20	<1	2	2	
Nickel	ppm	ASTM D5185m	>2	0	0	0	
Titanium	ppm	ASTM D5185m	>2	0	<1	0	
Silver	ppm	ASTM D5185m	>2	0	0	<1	
Aluminum	ppm	ASTM D5185m	>25	<1	<1	1	
Lead	ppm	ASTM D5185m	>40	<1	<1	<1	
Copper	ppm		>330	1	3	1	
Tin	ppm	ASTM D5185m	>15	<1	<1	0	
Vanadium	ppm	ASTM D5185m	>10	<1	<1	0	
Cadmium	ppm	ASTM D5185m		0	0	0	
ADDITIVES		method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m	0	6	6	8	
Barium	ppm	ASTM D5185m	0	0	0	0	
Molybdenum	ppm	ASTM D5185m	60	61	67	59	
Manganese	ppm		0	0	<1	<1	
Magnesium	ppm	ASTM D5185m	1010	1028	1070	983	
Calcium	ppm	ASTM D5185m	1070	1180	1232	1122	
Phosphorus	ppm	ASTM D5185m	1150	1069	1103	1063	
Zinc	ppm	ASTM D5185m	1270	1299	1328	1310	
Sulfur	ppm	ASTM D5185m	2060	3843	3740	3739	
CONTAMINAN	ITS	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>25	3	4	4	
Sodium	ppm	ASTM D5185m		2	16	2	
Potassium	ppm	ASTM D5185m	>20	<1	0	1	
INFRA-RED		method	limit/base	current	history1	history2	
Soot %	%	*ASTM D7844	>3	0.1	0.2	0.2	
Nitration	Abs/cm	*ASTM D7624		5.9	7.2	6.7	
Sulfation	Abs/.1mm	*ASTM D7415	>30	16.8	18.7	18.9	
FLUID DEGRADATION method limit/base current history1 history2							
Oxidation	Abs/.1mm	*ASTM D7414	>25	12.6	15.0	14.8	
Base Number (BN)	mg KOH/g	ASTM D2896		8.8	9.4	9.2	
Dase Mulliber (DIV)	ilig NOD/g	A3 1 W D2090	3.0	0.0	3.4	5.2	




OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROP	ERIIES	method			riistory i	History2
Visc @ 100°C	cSt	ASTM D445	15.4	13.6	13.5	13.5

GRAPHS













Certificate L2367

Laboratory Sample No. Test Package : FLEET

Lab Number Unique Number : 10645796

: GFL0086867 : 05949837

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received Diagnosed

: 13 Sep 2023 : 15 Sep 2023 Diagnostician : Wes Davis

GFL Environmental - 419 - Metro Saginaw

6950 N Michigan Saginaw, MI US 48604 Contact: Jeremy Hines jhines@gflenv.com

T: (800)684-1277

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)