




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
945029

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0071771	GFL0071749	---
Sample Date	Client Info	13 Sep 2023	08 Jun 2023	---
Machine Age	hrs	Client Info	6322	5608
Oil Age	hrs	Client Info	600	600
Oil Changed	Client Info	Changed	Not Changd	---
Sample Status		NORMAL	NORMAL	---

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >5	<1.0	<1.0	---
Glycol	WC Method	NEG	NEG	---

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >100	8	8	---
Chromium	ppm ASTM D5185m >20	<1	0	---
Nickel	ppm ASTM D5185m >4	<1	0	---
Titanium	ppm ASTM D5185m	<1	<1	---
Silver	ppm ASTM D5185m >3	0	0	---
Aluminum	ppm ASTM D5185m >20	3	1	---
Lead	ppm ASTM D5185m >40	3	0	---
Copper	ppm ASTM D5185m >330	9	5	---
Tin	ppm ASTM D5185m >15	1	<1	---
Vanadium	ppm ASTM D5185m	<1	0	---
Cadmium	ppm ASTM D5185m	<1	0	---

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 0	3	31	---
Barium	ppm ASTM D5185m 0	0	0	---
Molybdenum	ppm ASTM D5185m 60	54	51	---
Manganese	ppm ASTM D5185m 0	<1	<1	---
Magnesium	ppm ASTM D5185m 1010	549	564	---
Calcium	ppm ASTM D5185m 1070	1760	1695	---
Phosphorus	ppm ASTM D5185m 1150	688	792	---
Zinc	ppm ASTM D5185m 1270	979	997	---
Sulfur	ppm ASTM D5185m 2060	2776	3065	---

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >25	4	5	---
Sodium	ppm ASTM D5185m	9	5	---
Potassium	ppm ASTM D5185m >20	5	<1	---

INFRA-RED



method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >3	0.1	0.1	---
Nitration	Abs/cm *ASTM D7624 >20	10.4	8.4	---
Sulfation	Abs/.1mm *ASTM D7415 >30	21.9	19.1	---

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	19.0	15.8	---
Base Number (BN)	mg KOH/g ASTM D2896 9.8	4.1	8.4	---







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.9	14.7

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0071771 **Received** : 14 Sep 2023
Lab Number : **05951923** **Diagnosed** : 19 Sep 2023
Unique Number : 10647882 **Diagnostician** : Jonathan Hester
Test Package : FLEET

GFL Environmental - 883 - Orange City
 1378 South Volusia Ave
 Orange City, FL
 US 32763
 Contact: Kenneth Pearce
 kpearce@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)