


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id 3402M Component

Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

GAL)		May2021	Aug2021 Mar2023	May2023 Jun2023	Sep2023	
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0092935	GFL0055936	GFL0067558
Sample Date		Client Info		12 Sep 2023	23 Jun 2023	30 May 2023
Machine Age	hrs	Client Info		18134	17775	17600
Oil Age	hrs	Client Info		17775	589	599
Oil Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>110	15	16	11
Chromium	ppm	ASTM D5185m	>4	1	<1	<1
Nickel	ppm	ASTM D5185m	>2	<1	<1	<1
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m	>25	2	2	4
Lead	ppm	ASTM D5185m	>45	2	<1	<1
Copper	ppm	ASTM D5185m	>85	4	2	1
Tin	ppm	ASTM D5185m	>4	2	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		<1	<1	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	1	2	5
Barium	ppm	ASTM D5185m	0	44	<1	0
Molybdenum	ppm	ASTM D5185m	60	59	62	61
Manganese	ppm	ASTM D5185m	0	1	<1	<1
Magnesium	ppm	ASTM D5185m	1010	917	946	954
Calcium	ppm	ASTM D5185m	1070	1007	1101	1106
Phosphorus	ppm	ASTM D5185m	1150	955	1016	1067
Zinc	ppm	ASTM D5185m	1270	1183	1246	1322
Sulfur	ppm	ASTM D5185m	2060	3085	3624	3480
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>30	5	13	12
Sodium	ppm	ASTM D5185m		5	3	2
Potassium	ppm	ASTM D5185m	>20	2	2	3
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.7	0.3	0.2
Nitration	Abs/cm	*ASTM D7624	>20	9.5	8.0	6.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.4	19.0	18.4
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.8	15.2	14.3
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.8	9.5	9.3
Dage Hamber (DIV)	ing Noring	7.0 TW D2000	0.0	0.0	0.0	0.0



OIL ANALYSIS REPORT





19 Abnormal					
17-					
16 - Base					
16 Base 15					
14-					
13 - Abnormal	<u></u>				
12-					
11		-	-	-	
May11/21		Mar13/23	May30/23	23	


VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROP	ERIIES	method			riistory i	History
Visc @ 100°C	cSt	ASTM D445	15.4	13.7	13.7	13.6

GRAPHS













Certificate L2367

Laboratory Sample No. Lab Number Unique Number : 10648485 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0092935 : 05952526

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received

: 15 Sep 2023 Diagnosed Diagnostician : Wes Davis

: 18 Sep 2023

GFL Environmental - 463 - Cheboygan 501 N. Western Ave Cheboygan, MI US 49721 Contact: Chris Gee

cgee@gflenv.com T: (231)597-8553

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)