




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
427075-402234
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0067106	GFL0079372	GFL0067078
Sample Date	Client Info	01 Sep 2023	11 May 2023	21 Feb 2023
Machine Age	hrs	38551	37763	37183
Oil Age	hrs	588	580	700
Oil Changed	Client Info	Changed	Changed	Changed
Sample Status		NORMAL	ABNORMAL	ABNORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >3.0	<1.0	<1.0	<1.0
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >120	36	51	64
Chromium	ppm ASTM D5185m >20	1	2	<1
Nickel	ppm ASTM D5185m >5	<1	<1	0
Titanium	ppm ASTM D5185m >2	0	<1	0
Silver	ppm ASTM D5185m >2	0	<1	0
Aluminum	ppm ASTM D5185m >20	2	2	1
Lead	ppm ASTM D5185m >40	2	3	<1
Copper	ppm ASTM D5185m >330	7	4	5
Tin	ppm ASTM D5185m >15	1	1	0
Vanadium	ppm ASTM D5185m	0	0	0
Cadmium	ppm ASTM D5185m	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 0	0	2	0
Barium	ppm ASTM D5185m 0	0	0	0
Molybdenum	ppm ASTM D5185m 60	60	55	54
Manganese	ppm ASTM D5185m 0	<1	1	0
Magnesium	ppm ASTM D5185m 1010	886	901	874
Calcium	ppm ASTM D5185m 1070	1038	1017	1003
Phosphorus	ppm ASTM D5185m 1150	971	964	947
Zinc	ppm ASTM D5185m 1270	1166	1188	1153
Sulfur	ppm ASTM D5185m 2060	3083	3212	2797

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >25	3	3	2
Sodium	ppm ASTM D5185m	<1	2	0
Potassium	ppm ASTM D5185m >20	<1	2	0

INFRA-RED



method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >4	3.2	▲ 5	▲ 4.1
Nitration	Abs/cm *ASTM D7624 >20	8.1	10.3	9.4
Sulfation	Abs/.1mm *ASTM D7415 >30	22.6	27.1	24.9

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	12.8	14.4	14.3
Base Number (BN)	mg KOH/g ASTM D2896 9.8	7.7	▲ 0.0	5.6







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	14.3	15.4	14.5

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0067106 **Received** : 19 Sep 2023
Lab Number : **05955048** **Diagnosed** : 20 Sep 2023
Unique Number : 10656261 **Diagnostician** : Wes Davis
Test Package : FLEET

GFL Environmental - 822 - Springfield Hauling
 2120 West Bennett Street
 Springfield, MO
 US 65807
 Contact: Dennis Moore
 dennis.moore@gflenv.com
 T: (417)403-3641
 F:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)