

OIL ANALYSIS REPORT





Component Diesel Engine Fluid

PETRO CANADA DURON SHP 10W30 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

Metal levels are typical for a components first oil change.

Contamination

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


AL)				Sep2023		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0105311		
Sample Date		Client Info		12 Sep 2023		
Machine Age	mls	Client Info		59898		
Dil Age	mls	Client Info		59898		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Glycol		WC Method		NEG		
WEAR METAL	.S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	62		
Chromium	ppm	ASTM D5185m		3		
Nickel	ppm	ASTM D5185m	>4			
Titanium	ppm	ASTM D5185m	e 1	<1		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m		18		
Lead	ppm	ASTM D5185m	>40	<1		
Copper	ppm	ASTM D5185m		45		
Tin	ppm	ASTM D5185m	>15	3		
Vanadium	ppm	ASTM D5185m	210	0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES	ppm	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	3		
Barium	ppm	ASTM D5185m	0	0		
Molybdenum	ppm	ASTM D5185m	50	70		
Manganese	ppm	ASTM D5185m	0	1		
Magnesium	ppm	ASTM D5185m	950	988		
Calcium	ppm	ASTM D5185m	1050	1313		
Phosphorus	ppm	ASTM D5185m	995	1033		
Zinc	ppm	ASTM D5185m	1180	1308		
Sulfur	ppm	ASTM D5185m	2600	2548		
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	8		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m		44		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	1.9		
Nitration	Abs/cm	*ASTM D7624	>20	12.7		
	Abs/.1mm	*ASTM D7415	>30	25.3		
Sulfation	ADS/.IIIIII					
Sulfation FLUID DEGRA		method	limit/base	current	history1	history2
Sulfation FLUID DEGRA Oxidation		method *ASTM D7414		current 23.4	history1	history2





OIL ANALYSIS REPORT











Laboratory

Sample No.

Lab Number

T: (215)552-9832

F: (215)552-9892