

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id 738606

Component Diesel Engine

Fluid PETRO CANADA DURON SHP 10W30 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORM	/IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0105300	PCA0093248	PCA0090119
Sample Date		Client Info		01 Sep 2023	22 Feb 2023	10 Feb 2023
Machine Age	mls	Client Info		191794	40502	160000
Oil Age	mls	Client Info		191794	40502	0
Oil Changed		Client Info		Changed	Changed	N/A
Sample Status				NORMAL	NORMAL	ABNORMAL
CONTAMINATI	ON	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	93	66	1 29
Chromium	ppm	ASTM D5185m	>20	4	3	5
Nickel	ppm	ASTM D5185m	>4	<1	<1	1
Titanium	ppm	ASTM D5185m		9	26	5
Silver	ppm	ASTM D5185m	>3	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	17	20	41
Lead	ppm	ASTM D5185m	>40	<1	0	<1
Copper	ppm	ASTM D5185m	>330	29	60	50
Tin	ppm	ASTM D5185m	>15	2	2	2
Vanadium	ppm	ASTM D5185m		0	<1	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	3	18	3
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	50	62	39	61
Manganese	ppm	ASTM D5185m	0	2	2	2
Magnesium	ppm	ASTM D5185m	950	921	635	891
Calcium	ppm	ASTM D5185m	1050	1400	1508	1425
Phosphorus	ppm	ASTM D5185m	995	1082	903	928
Zinc	ppm	ASTM D5185m	1180	1367	1122	1204
Sulfur	ppm	ASTM D5185m	2600	2965	2507	2206
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	9	8	10
Sodium	ppm	ASTM D5185m		2	<1	4
Potassium	ppm	ASTM D5185m	>20	32	50	98
					In the American Market	histow.0
INFRA-RED		method	limit/base	current	history1	history2
INFRA-RED Soot %	%	method *ASTM D7844	limit/base	current 1.8	1.3	2.1
	% Abs/cm					
Soot %		*ASTM D7844	>3 >20	1.8	1.3	2.1
Soot % Nitration	Abs/cm Abs/.1mm	*ASTM D7844 *ASTM D7624	>3 >20	1.8 14.6	1.3 12.0	2.1 20.5
Soot % Nitration Sulfation	Abs/cm Abs/.1mm	*ASTM D7844 *ASTM D7624 *ASTM D7415	>3 >20 >30 limit/base	1.8 14.6 27.3	1.3 12.0 25.0	2.1 20.5 33.2



OIL ANALYSIS REPORT





Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Laboratory

Sample No.

Lab Number

Contact/Location: ROSTY VITER - MILPHINE

F: (215)552-9892