




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
10160

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (32 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0087757	GFL0087750	GFL0082263
Sample Date	Client Info	19 Sep 2023	14 Sep 2023	01 Jun 2023
Machine Age	hrs	35762	35680	31727
Oil Age	hrs	500	600	300
Oil Changed	Client Info	Not Changed	Changed	Not Changed
Sample Status		NORMAL	NORMAL	MARGINAL

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >2.0	<1.0	<1.0	▲ 2.8
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >100	7	24	18
Chromium	ppm ASTM D5185m >20	<1	2	<1
Nickel	ppm ASTM D5185m >4	0	<1	0
Titanium	ppm ASTM D5185m	0	<1	0
Silver	ppm ASTM D5185m >3	0	0	0
Aluminum	ppm ASTM D5185m >20	<1	2	1
Lead	ppm ASTM D5185m >40	3	15	13
Copper	ppm ASTM D5185m >330	<1	3	2
Tin	ppm ASTM D5185m >15	<1	2	<1
Vanadium	ppm ASTM D5185m	0	0	0
Cadmium	ppm ASTM D5185m	0	<1	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 0	0	3	7
Barium	ppm ASTM D5185m 0	0	44	0
Molybdenum	ppm ASTM D5185m 60	63	63	68
Manganese	ppm ASTM D5185m 0	<1	1	<1
Magnesium	ppm ASTM D5185m 1010	1070	944	988
Calcium	ppm ASTM D5185m 1070	1224	1119	1351
Phosphorus	ppm ASTM D5185m 1150	1101	1011	1086
Zinc	ppm ASTM D5185m 1270	1354	1268	1367
Sulfur	ppm ASTM D5185m 2060	3815	3296	3832

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >25	2	4	3
Sodium	ppm ASTM D5185m	5	12	11
Potassium	ppm ASTM D5185m >20	3	5	2

INFRA-RED



method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >3	0.2	0.3	0.2
Nitration	Abs/cm *ASTM D7624 >20	7.4	11.5	12.9
Sulfation	Abs/.1mm *ASTM D7415 >30	19.6	24.3	26.9

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	15.9	22.9	28.1
Base Number (BN)	mg KOH/g ASTM D2896 9.8	8.5	6.9	6.4







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	13.3	13.8	13.8

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0087757
Lab Number : **05957431**
Unique Number : 10658644
Test Package : FLEET

GFL Environmental - 006 - Wilmington
 3618 US Highway 421 N
 Wilmington, NC
 US 28401
 Contact: Eric Wood
 eric.wood@gflenv.com
 T: (717)723-1956
 F: (910)762-6880

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)