


# OIL ANALYSIS REPORT

Sample Rating Trend



**NORMAL**



Area  
**Off-Road**  
Machine Id  
**E64**  
Component  
**Diesel Engine**  
Fluid  
**PETRO CANADA DURON SHP 15W40 (--- GAL)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>PCA0090499</b>	PCA0090494	PCA0083080
Sample Date	Client Info		<b>20 Sep 2023</b>	26 Jul 2023	29 Mar 2023
Machine Age	hrs	Client Info	<b>14007</b>	14007	13499
Oil Age	hrs	Client Info	<b>10314</b>	10822	10579
Oil Changed	Client Info		<b>N/A</b>	N/A	N/A
Sample Status			<b>NORMAL</b>	NORMAL	NORMAL

## CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<b>&lt;1.0</b>	<1.0	0.5
Glycol	WC Method		<b>NEG</b>	NEG	NEG

## WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >100	<b>29</b>	54	22
Chromium	ppm	ASTM D5185m >20	<b>&lt;1</b>	<1	0
Nickel	ppm	ASTM D5185m >2	<b>0</b>	0	0
Titanium	ppm	ASTM D5185m >2	<b>0</b>	0	0
Silver	ppm	ASTM D5185m >2	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m >25	<b>1</b>	<1	<1
Lead	ppm	ASTM D5185m >40	<b>&lt;1</b>	9	0
Copper	ppm	ASTM D5185m >330	<b>1</b>	2	0
Tin	ppm	ASTM D5185m >15	<b>0</b>	0	0
Vanadium	ppm	ASTM D5185m	<b>0</b>	<1	0
Cadmium	ppm	ASTM D5185m	<b>0</b>	0	0

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	<b>8</b>	14	14
Barium	ppm	ASTM D5185m 0	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m 60	<b>62</b>	74	66
Manganese	ppm	ASTM D5185m 0	<b>0</b>	<1	<1
Magnesium	ppm	ASTM D5185m 1010	<b>980</b>	1131	1098
Calcium	ppm	ASTM D5185m 1070	<b>1216</b>	1354	1329
Phosphorus	ppm	ASTM D5185m 1150	<b>1027</b>	1144	1151
Zinc	ppm	ASTM D5185m 1270	<b>1310</b>	1460	1413
Sulfur	ppm	ASTM D5185m 2060	<b>3627</b>	3754	3833

## CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	<b>7</b>	10	7
Sodium	ppm	ASTM D5185m	<b>3</b>	2	2
Potassium	ppm	ASTM D5185m >20	<b>3</b>	0	0



## INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	<b>1</b>	1.4	0.7
Nitration	Abs/cm	*ASTM D7624 >20	<b>8.1</b>	10.8	7.7
Sulfation	Abs/.1mm	*ASTM D7415 >30	<b>20.9</b>	24.1	20.6

## FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	<b>16.0</b>	20.3	15.2
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	<b>10.17</b>	8.96	9.46









# OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	12.6	13.1

## GRAPHS



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : PCA0090499 **Received** : 22 Sep 2023  
**Lab Number** : 05958736 **Diagnosed** : 25 Sep 2023  
**Unique Number** : 10659949 **Diagnostician** : Wes Davis  
**Test Package** : MOB 2

**WIN Waste Innovations - Shop # - Taunton**  
 565 WINTHROP ST  
 TAUNTON, MA  
 US 02780  
 Contact: Dave Wilson  
 dwilson@win-waste.com  
 T:  
 F:

Certificate L2367  
 To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)