

OIL ANALYSIS REPORT

Sample Rating Trend





Component Diesel Engine Fluid

PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Februar Aughars Jundars Jundars Jundars September											
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2					
Sample Number		Client Info		GFL0091216	GFL0070603	GFL0087807					
Sample Date		Client Info		28 Sep 2023	12 Jul 2023	27 Jun 2023					
Machine Age	mls	Client Info		240857	240738	235087					
Dil Age	mls	Client Info		0	0	235087					
Oil Changed		Client Info		Not Changd	Changed	Not Changd					
Sample Status				NORMAL	NORMAL	NORMAL					
CONTAMINATI	ION	method	limit/base	current	history1	history2					
Fuel		WC Method	>5	<1.0	<1.0	<1.0					
Glycol		WC Method		NEG	NEG	NEG					
WEAR METAL	S	method	limit/base	current	history1	history2					
Iron	ppm	ASTM D5185m	>100	4	8	7					
Chromium	ppm	ASTM D5185m	>20	0	<1	0					
Nickel	ppm	ASTM D5185m	>4	0	0	0					
Titanium	ppm	ASTM D5185m		0	0	0					
Silver	ppm	ASTM D5185m	>3	0	0	0					
Aluminum	ppm	ASTM D5185m	>20	3	2	2					
Lead	ppm	ASTM D5185m	>40	0	0	<1					
Copper	ppm	ASTM D5185m	>330	<1	<1	1					
Tin	ppm	ASTM D5185m	>15	0	0	<1					
Vanadium	ppm	ASTM D5185m		0	0	0					
Cadmium	ppm	ASTM D5185m		0	0	0					
ADDITIVES		method	limit/base	current	history1	history2					
Boron	ppm	ASTM D5185m	0	8	41	44					
Barium	ppm	ASTM D5185m	0	0	0	2					
Molybdenum	ppm	ASTM D5185m	60	64	69	69					
Manganese	ppm	ASTM D5185m	0	0	<1	<1					
Magnesium	ppm	ASTM D5185m	1010	914	963	795					
Calcium	ppm	ASTM D5185m	1070	1017	1150	1117					
Phosphorus	ppm	ASTM D5185m	1150	1041	1059	991					
Zinc	ppm	ASTM D5185m	1270	1237	1307	1111					
Sulfur	ppm	ASTM D5185m	2060	3586	3876	3026					
CONTAMINAN	TS	method	limit/base	current	history1	history2					
Silicon	ppm	ASTM D5185m	>25	3	4	3					
Sodium	ppm	ASTM D5185m		2	4	0					
Potassium	ppm	ASTM D5185m	>20	1	0	2					
INFRA-RED		method	limit/base	current	history1	history2					
Soot %	%	*ASTM D7844	>3	0.2	0.5	0.5					
Nitration	Abs/cm	*ASTM D7624	>20	4.9	6.2	6.2					
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.2	18.5	19.1					
FLUID DEGRAD	DATION	method	limit/base	current	history1	history2					
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.5	13.9	15.3					
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	9.7	9.5	9.3					



OIL ANALYSIS REPORT

VISUAL



Laboratory Sample No. Lab Number Unique Number Test Package				Oct 2023 Oct 2023 s Davis	18 Old Brickyard R 123 Phenix City, A			
	CZ081rep Viscosity @ 100°C Abnormal CZ081rep CZ081re		Jun27/23	10.0 8eb58/233 8eb58/233 8ec Minuper (jud KoH(0) 8ec 2.0 8c 2.0 8	Base Number	Jan 26/23 Apri 10/23 Apri 10/23	Juni21/23	
	Ferrous Alloys		Jun27/23	Sep28/23				
	FLUID PROPE Visc @ 100°C GRAPHS		method ASTM D445	limit/base 15.4	current	history1 14.2	history2 14.2	
	Emulsified Water Free Water	scalar scalar	*Visual *Visual	>0.2	NEG NEG	NEG NEG	NEG NEG	
Jul12/23 + Sep28/23 +	Sand/Dirt Appearance Odor	scalar	*Visual *Visual *Visual	NONE NORML NORML	NONE NORML NORML	NONE NORML NORML	NONE NORML NORML	
	Precipitate Silt Debris	scalar	*Visual *Visual *Visual	NONE NONE NONE	NONE NONE NONE	NONE NONE NONE	NONE NONE NONE	
	Yellow Metal		*Visual *Visual	NONE	NONE NONE	NONE NONE	NONE	

To discuss this sa * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Submitted By: DARRIN WRIGHT

F: