


OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
FREIGHTLINER 51

Component
Diesel Engine

Fluid
PETRO CANADA DURON HP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			PCA0096659	PCA0076809	---
Sample Date	Client Info			27 Sep 2023	14 Jul 2022	---
Machine Age	mls	Client Info		453264	446796	---
Oil Age	mls	Client Info		28144	29055	---
Oil Changed	Client Info			Changed	Changed	---
Sample Status				NORMAL	NORMAL	---

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method	>5		<1.0	<1.0	---
Glycol	WC Method			NEG	NEG	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	13	17	---
Chromium	ppm	ASTM D5185m	>5	<1	1	---
Nickel	ppm	ASTM D5185m	>2	0	0	---
Titanium	ppm	ASTM D5185m		1	30	---
Silver	ppm	ASTM D5185m	>3	0	<1	---
Aluminum	ppm	ASTM D5185m	>30	4	5	---
Lead	ppm	ASTM D5185m	>30	<1	<1	---
Copper	ppm	ASTM D5185m	>150	2	3	---
Tin	ppm	ASTM D5185m	>5	<1	<1	---
Vanadium	ppm	ASTM D5185m		<1	<1	---
Cadmium	ppm	ASTM D5185m		0	0	---



ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		3	20	---
Barium	ppm	ASTM D5185m		0	0	---
Molybdenum	ppm	ASTM D5185m		64	12	---
Manganese	ppm	ASTM D5185m		<1	<1	---
Magnesium	ppm	ASTM D5185m		1090	649	---
Calcium	ppm	ASTM D5185m		1291	1476	---
Phosphorus	ppm	ASTM D5185m		1107	1006	---
Zinc	ppm	ASTM D5185m		1441	1249	---
Sulfur	ppm	ASTM D5185m		3025	3418	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	5	6	---
Sodium	ppm	ASTM D5185m		3	2	---
Potassium	ppm	ASTM D5185m	>20	3	4	---

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.8	1	---
Nitration	Abs/cm	*ASTM D7624	>20	9.4	11.1	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.1	27.8	---

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.0	19.9	---
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.6	7.5	---









OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.6	14.5	15.5

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0096659 **Received** : 04 Oct 2023
Lab Number : **05968589** **Diagnosed** : 04 Oct 2023
Unique Number : 10675140 **Diagnostician** : Wes Davis
Test Package : MOB 1 (Additional Tests: TBN)

AREA WIDE TRANSPORTATION
 3085 IL RT 71
 OTTAWA, IL
 US 61350
 Contact: JEFF
 jeff@driveawt.com
 T: (815)587-2947
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)