

# **OIL ANALYSIS REPORT**

Sample Rating Trend





#### Component Diesel Engine

Fluid PETRO CANADA DURON SHP 10W30 (--- GAL)

# DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

## Wear

Metal levels are typical for a new component breaking in.

#### Contamination

There is no indication of any contamination in the oil.


#### Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

GAL)		Jun2020	Oct2020 Dec2020	Aug2021 Sep2021 Aug2023	Sep2023	
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0105325	PCA0100800	PCA0057123
Sample Date		Client Info		29 Sep 2023	16 Aug 2023	24 Sep 2021
Machine Age	mls	Client Info		52205	142508	3631
Oil Age	mls	Client Info		52205	142508	3631
Oil Changed		Client Info		Changed	Not Changd	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	60	24	20
Chromium	ppm	ASTM D5185m	>20	5	3	1
Nickel	ppm	ASTM D5185m	>4	<1	0	<1
Titanium	ppm	ASTM D5185m		4	17	<1
Silver	ppm	ASTM D5185m	>3	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	27	18	11
Lead	ppm	ASTM D5185m	>40	0	0	<1
Copper	ppm	ASTM D5185m	>330	13	14	48
Tin	ppm	ASTM D5185m	>15	<1	<1	4
Antimony	ppm	ASTM D5185m				0
Vanadium	ppm	ASTM D5185m		<1	<1	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	<1	9	8
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	50	61	68	60
Manganese	ppm	ASTM D5185m	0	1	0	<1
Magnesium	ppm	ASTM D5185m	950	983	1078	886
Calcium	ppm	ASTM D5185m	1050	1412	1584	1131
Phosphorus	ppm	ASTM D5185m	995	1069	1213	892
Zinc	ppm	ASTM D5185m	1180	1387	1672	1210
Sulfur	ppm	ASTM D5185m	2600	2747	4731	2386
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	7	3	2
Sodium	ppm	ASTM D5185m		4	<1	2
Potassium	ppm	ASTM D5185m	>20	26	20	23
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	1.5	0.7	0.5
Nitration	Abs/cm	*ASTM D7624	>20	11.3	8.8	8.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	25.3	21.6	21
FLUID DEGRAD	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.3	16.6	16.6
Base Number (BN)	mg KOH/g	ASTM D2896		4.8	6.7	



# **OIL ANALYSIS REPORT**





Certificate L2367

Laboratory

Contact/Location: ROSTY VITER - MILPHINE