

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL




Area KEMP QUARRIES / PRYOR STONE [66213] WL138 Component

Rear Right Final Drive

PETRO CANADA PRODURO TO-4 SAE 50 (--- GAL)

SAMPLE INFORMATION method





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment: Pm2 performed. All oil samples taken. Engine oil, transmission oil, and all filters changed.)

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition


The condition of the oil is acceptable for the time in service.

					Thotory	motory
Sample Number		Client Info		PCA0084273	PCA0084540	PCA0083959
Sample Date		Client Info		25 Sep 2023	26 Jul 2023	09 May 2023
Machine Age	hrs	Client Info		32588	32144	31544
Oil Age	hrs	Client Info		1044	32144	2205
Oil Changed		Client Info		Oil Added	N/A	Changed
Sample Status				NORMAL	NORMAL	NORMAL
			11 11 11			-
WEAR METAL	.5	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>800	11	11	15
Chromium	ppm	ASTM D5185m	>10	0	<1	<1
Nickel	ppm	ASTM D5185m	>5	0	0	<1
Titanium	ppm	ASTM D5185m	>15	0	<1	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>75	0	<1	3
Lead	ppm	ASTM D5185m	>10	<1	0	0
Copper	ppm	ASTM D5185m	>75	1	1	1
Tin	ppm	ASTM D5185m	>8	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	<1	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	4	0	<1
Barium	ppm	ASTM D5185m	0	4	0	0
Molybdenum		ASTM D5185m	0	7	6	8
Manganese	ppm ppm		0	، <1	<1	<1
Magnesium		ASTM D5185m	9	21	15	22
Calcium	ppm ppm	ASTM D5185m	9 3114	3579	3684	3303
Phosphorus		ASTM D5185m	1099	954	967	1037
Zinc	ppm	ASTM D5185m	1245	1187	1161	1282
Sulfur	ppm	ASTM D5185m	7086	4819	4869	5046
	ppm	ASTIVI DOTODITI	7000	4019	4009	5046
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>400	18	19	19
Sodium	ppm	ASTM D5185m		<1	<1	2
Potassium	ppm	ASTM D5185m	>20	0	0	1
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	213.9	194	193	180
21:19) Rev: 1	001					Submitted By



OIL ANALYSIS REPORT





Certificate L2367

Ĕ