




# OIL ANALYSIS REPORT

Sample Rating Trend



**NORMAL**



Machine Id  
**492M**  
Component  
**Diesel Engine**  
Fluid  
**PETRO CANADA DURON SHP 15W40 (--- GAL)**

## DIAGNOSIS

### Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

Fuel content negligible. There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

|               | method      | limit/base  | current            | history1    | history2    |
|---------------|-------------|-------------|--------------------|-------------|-------------|
| Sample Number | Client Info |             | <b>GFL0093126</b>  | GFL0081372  | GFL0057398  |
| Sample Date   | Client Info |             | <b>12 Oct 2023</b> | 18 May 2023 | 18 Oct 2022 |
| Machine Age   | hrs         | Client Info | <b>26901</b>       | 25986       | 24815       |
| Oil Age       | hrs         | Client Info | <b>25986</b>       | 24815       | 0           |
| Oil Changed   | Client Info |             | <b>Changed</b>     | Changed     | Changed     |
| Sample Status |             |             | <b>NORMAL</b>      | SEVERE      | SEVERE      |

## CONTAMINATION

|        | method    | limit/base | current    | history1 | history2 |
|--------|-----------|------------|------------|----------|----------|
| Glycol | WC Method |            | <b>NEG</b> | NEG      | NEG      |

## WEAR METALS

|          | method | limit/base       | current      | history1 | history2 |
|----------|--------|------------------|--------------|----------|----------|
| Iron     | ppm    | ASTM D5185m >90  | <b>10</b>    | 17       | 28       |
| Chromium | ppm    | ASTM D5185m >20  | <b>&lt;1</b> | 1        | 1        |
| Nickel   | ppm    | ASTM D5185m >2   | <b>0</b>     | <1       | 0        |
| Titanium | ppm    | ASTM D5185m >2   | <b>0</b>     | 0        | 0        |
| Silver   | ppm    | ASTM D5185m >2   | <b>0</b>     | 0        | 0        |
| Aluminum | ppm    | ASTM D5185m >20  | <b>3</b>     | 4        | 3        |
| Lead     | ppm    | ASTM D5185m >40  | <b>&lt;1</b> | 3        | 2        |
| Copper   | ppm    | ASTM D5185m >330 | <b>&lt;1</b> | 0        | 6        |
| Tin      | ppm    | ASTM D5185m >15  | <b>&lt;1</b> | <1       | <1       |
| Antimony | ppm    | ASTM D5185m      | <b>---</b>   | ---      | ---      |
| Vanadium | ppm    | ASTM D5185m      | <b>0</b>     | 0        | 0        |
| Cadmium  | ppm    | ASTM D5185m      | <b>0</b>     | 0        | 0        |

## ADDITIVES

|            | method | limit/base       | current      | history1 | history2 |
|------------|--------|------------------|--------------|----------|----------|
| Boron      | ppm    | ASTM D5185m 0    | <b>5</b>     | 4        | 5        |
| Barium     | ppm    | ASTM D5185m 0    | <b>0</b>     | 0        | 0        |
| Molybdenum | ppm    | ASTM D5185m 60   | <b>65</b>    | 60       | 53       |
| Manganese  | ppm    | ASTM D5185m 0    | <b>&lt;1</b> | <1       | <1       |
| Magnesium  | ppm    | ASTM D5185m 1010 | <b>1037</b>  | 935      | 786      |
| Calcium    | ppm    | ASTM D5185m 1070 | <b>1187</b>  | 1064     | 924      |
| Phosphorus | ppm    | ASTM D5185m 1150 | <b>1019</b>  | 1020     | 860      |
| Zinc       | ppm    | ASTM D5185m 1270 | <b>1382</b>  | 1307     | 1069     |
| Sulfur     | ppm    | ASTM D5185m 2060 | <b>3047</b>  | 3423     | 2652     |

## CONTAMINANTS

|           | method | limit/base      | current      | history1 | history2 |
|-----------|--------|-----------------|--------------|----------|----------|
| Silicon   | ppm    | ASTM D5185m >25 | <b>4</b>     | 5        | 6        |
| Sodium    | ppm    | ASTM D5185m     | <b>2</b>     | 17       | 7        |
| Potassium | ppm    | ASTM D5185m >20 | <b>&lt;1</b> | 2        | 0        |
| Fuel      | %      | ASTM D3524 >3.0 | <b>0.9</b>   | 10.7     | 7.9      |

## INFRA-RED




|           | method   | limit/base      | current     | history1 | history2 |
|-----------|----------|-----------------|-------------|----------|----------|
| Soot %    | %        | *ASTM D7844 >6  | <b>0.2</b>  | 0.3      | 0.6      |
| Nitration | Abs/cm   | *ASTM D7624 >20 | <b>9.0</b>  | 11.5     | 11.2     |
| Sulfation | Abs/.1mm | *ASTM D7415 >30 | <b>21.3</b> | 22.9     | 25.0     |

## FLUID DEGRADATION

|                  | method   | limit/base      | current     | history1 | history2 |
|------------------|----------|-----------------|-------------|----------|----------|
| Oxidation        | Abs/.1mm | *ASTM D7414 >25 | <b>18.7</b> | 23.1     | 23.0     |
| Base Number (BN) | mg KOH/g | ASTM D2896 9.8  | <b>9.1</b>  | 7.3      | 6.8      |







# OIL ANALYSIS REPORT



| VISUAL           | method | limit/base | current | history1 | history2 |
|------------------|--------|------------|---------|----------|----------|
| White Metal      | scalar | *Visual    | NONE    | NONE     | NONE     |
| Yellow Metal     | scalar | *Visual    | NONE    | NONE     | NONE     |
| Precipitate      | scalar | *Visual    | NONE    | NONE     | NONE     |
| Silt             | scalar | *Visual    | NONE    | NONE     | NONE     |
| Debris           | scalar | *Visual    | NONE    | NONE     | NONE     |
| Sand/Dirt        | scalar | *Visual    | NONE    | NONE     | NONE     |
| Appearance       | scalar | *Visual    | NORML   | NORML    | NORML    |
| Odor             | scalar | *Visual    | NORML   | NORML    | NORML    |
| Emulsified Water | scalar | *Visual    | >0.2    | NEG      | NEG      |
| Free Water       | scalar | *Visual    |         | NEG      | NEG      |

| FLUID PROPERTIES | method | limit/base | current | history1    | history2      |
|------------------|--------|------------|---------|-------------|---------------|
| Visc @ 100°C     | cSt    | ASTM D445  | 15.4    | <b>15.2</b> | ▲ 12.4 ▲ 11.4 |

## GRAPHS



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0093126 **Received** : 16 Oct 2023  
**Lab Number** : 05979296 **Diagnosed** : 17 Oct 2023  
**Unique Number** : 10696591 **Diagnostician** : Wes Davis  
**Test Package** : FLEET ( Additional Tests: PercentFuel )

**GFL Environmental - 415 - Michigan East**  
 6200 Elmridge  
 Sterling Heights, MI  
 US 48313  
 Contact: Frank Wolak  
 fwolak@gflenv.com  
 T: (586)825-9514  
 F:

Certificate L2367  
 To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)