


OIL ANALYSIS REPORT

(89640X) Walgreens - Tractor [Walgreens - Tractor] 136A68028

Diesel Engine

PETRO CANADA DURON SHP 10W30 (11 GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

GAL)			Jun2023	Oct2023		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0093517	PCA0093506	
Sample Date		Client Info		03 Oct 2023	01 Jun 2023	
Machine Age	mls	Client Info		209583	198918	
Oil Age	mls	Client Info		29283	198918	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	
Glycol		WC Method		NEG	NEG	
WEAR METAL	.S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	25	40	
Chromium	ppm	ASTM D5185m	>5	<1	2	
Nickel	ppm	ASTM D5185m	>2	0	0	
Titanium	ppm	ASTM D5185m		14	4	
Silver	ppm	ASTM D5185m	>3	0	0	
Aluminum	ppm	ASTM D5185m	>30	3	2	
Lead	ppm	ASTM D5185m	>30	0	0	
Copper	ppm	ASTM D5185m	>150	2	2	
Tin	ppm	ASTM D5185m	>5	 <1	<1	
Vanadium	ppm	ASTM D5185m		<1	<1	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	11	10	
Barium	ppm	ASTM D5185m	0	0	0	
Molybdenum	ppm	ASTM D5185m	50	45	51	
Manganese	ppm	ASTM D5185m	0	<1	<1	
Magnesium	ppm	ASTM D5185m	950	768	849	
Calcium	ppm	ASTM D5185m	1050	1198	1242	
Phosphorus	ppm	ASTM D5185m	995	830	981	
Zinc	ppm	ASTM D5185m	1180	1158	1248	
Sulfur	ppm	ASTM D5185m	2600	2845	3611	
CONTAMINAN	ITS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	7	9	
Sodium	ppm	ASTM D5185m		2	2	
Potassium	ppm	ASTM D5185m	>20	2	1	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.5	0.6	
Nitration	Abs/cm	*ASTM D7624	>20	10.6	11.9	
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.2	24.7	
FLUID DEGRAI	OITAC	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	19.3	23.7	
Base Number (BN)	mg KOH/g		>20	5.9	4.9	
Dase Mulliber (DIN)	my Normy	AO INI DZ030		5.5	4.0	





OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	
FLUID PROPE	DTIES	method	limit/hase	current	history1	history2

FLUID PROPI	ERITES	method	limit/base		history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	11.2	11.3	











Certificate L2367

Laboratory Sample No. Lab Number Unique Number : 10696596 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : PCA0093517 : 05979301

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received Diagnosed

: 16 Oct 2023 : 17 Oct 2023 Diagnostician : Wes Davis

Transervice - Shop 1376 - Berkeley-Linden 3425 Tremley Point Road

Linden, NJ US 07036 Contact: Shop 1376 Oil Analysis

shop1376@transervice.com

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: