

OIL ANALYSIS REPORT

Sample Rating Trend


NORMAL



KEMP QUARRIES / KEMP STONE - FAIRLAND [66473] **WL128**

Component **Rear Right Final Drive**

PETRO CANADA PRODURO TO-4 SAE 50 (--- GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment: PM-3 sampled fluid)

All component wear rates are normal.

Contamination

There is no indication of any contamination in the

Fluid Condition

The condition of the oil is acceptable for the time in service.

RO TO-4 SAE 50 ((GAL)	Vlar2019 Jan	2020 Jul2020 Jan20.	21 Jun2022 Nov2022 Apr20	23 Oct2023	
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PCA0084758	PCA0084612	PCA0086003
Sample Date		Client Info		06 Oct 2023	10 Jul 2023	20 Apr 2023
Machine Age	hrs	Client Info		34458	33887	33426
Oil Age	hrs	Client Info		34458	33887	33426
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
WEAR METAI	LS	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>800	308	325	194
Chromium	ppm	ASTM D5185m	>10	3	<1	<1
Nickel	ppm	ASTM D5185m	>5	<1	<1	0
Titanium	ppm	ASTM D5185m	>15	<1	<1	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>75	4	4	2
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>75	2	2	<1
Tin	ppm	ASTM D5185m	>8	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	0	0	0
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	3	3	2
Manganese	ppm	ASTM D5185m	0	2	2	2
Magnesium	ppm	ASTM D5185m	9	15	17	17
Calcium	ppm	ASTM D5185m	3114	3316	3887	3288
Phosphorus	ppm	ASTM D5185m	1099	1001	1129	922
Zinc	ppm	ASTM D5185m	1245	1215	1392	1131
Sulfur	ppm	ASTM D5185m	7086	4793	5964	5187
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>400	37	42	33
Sodium	ppm	ASTM D5185m		0	0	<1
Potassium	ppm	ASTM D5185m	>20	2	1	0
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	LIGHT	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPE	ERTIES	method	limit/base	current	history1	history2

Visc @ 40°C

cSt

ASTM D445 213.9


192


191

192



OIL ANALYSIS REPORT









Certificate L2367

Laboratory Sample No. Lab Number **Unique Number** Test Package : MOB 1

: PCA0084758 : 05980730 : 10698025

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 16 Oct 2023 Diagnosed

: 18 Oct 2023 Diagnostician : Sean Felton Kemp Quarries - Kemp Stone - Fairland

18350 S 590 Rd Fairland, OK US 74343

no image

no image

Contact:

fairland@kempstone.com

T: F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)