




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
2729

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0094914	GFL0094930	GFL0088414
Sample Date	Client Info	10 Oct 2023	25 Sep 2023	29 Aug 2023
Machine Age	mls	Client Info	302502	296967
Oil Age	mls	Client Info	296967	274902
Oil Changed	Client Info	N/A	Changed	Changed
Sample Status		NORMAL	NORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >3.0	<1.0	<1.0	<1.0
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m >165	19	29	11
Chromium	ppm	ASTM D5185m >5	2	<1	<1
Nickel	ppm	ASTM D5185m >4	<1	5	0
Titanium	ppm	ASTM D5185m >2	<1	0	<1
Silver	ppm	ASTM D5185m >2	0	<1	0
Aluminum	ppm	ASTM D5185m >20	5	<1	5
Lead	ppm	ASTM D5185m >150	<1	<1	0
Copper	ppm	ASTM D5185m >90	<1	7	2
Tin	ppm	ASTM D5185m >5	<1	1	0
Vanadium	ppm	ASTM D5185m	0	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m 0	1	<1	0
Barium	ppm	ASTM D5185m 0	0	0	0
Molybdenum	ppm	ASTM D5185m 60	63	60	58
Manganese	ppm	ASTM D5185m 0	0	<1	<1
Magnesium	ppm	ASTM D5185m 1010	962	967	945
Calcium	ppm	ASTM D5185m 1070	1068	1124	1059
Phosphorus	ppm	ASTM D5185m 1150	1034	984	1022
Zinc	ppm	ASTM D5185m 1270	1268	1303	1245
Sulfur	ppm	ASTM D5185m 2060	3349	2611	3627

CONTAMINANTS

method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m >35	8	5	9
Sodium	ppm	ASTM D5185m	5	2	4
Potassium	ppm	ASTM D5185m >20	11	5	5

INFRA-RED



method	limit/base	current	history1	history2	
Soot %	%	*ASTM D7844 >7.5	0.3	1.3	0.2
Nitration	Abs/cm	*ASTM D7624 >20	9.4	9.0	7.2
Sulfation	Abs/.1mm	*ASTM D7415 >30	21.0	21.9	19.3

FLUID DEGRADATION

method	limit/base	current	history1	history2	
Oxidation	Abs/.1mm	*ASTM D7414 >25	17.8	16.7	15.2
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	7.4	7.1	8.3







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	13.4	13.8	13.8

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : GFL0094914 Received : 17 Oct 2023
 Lab Number : **05981831** Diagnosed : 18 Oct 2023
 Unique Number : 10699126 Diagnostician : Wes Davis
 Test Package : FLEET

GFL Environmental - 084 - Clarksville
 699 Jack Miller Boulevard
 Clarksville, TN
 US 37042
 Contact: ROBERT THIBAUT
 robert.thibault@gflenv.com
 T: (931)552-7276
 F: (931)572-9674

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)