


OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id **928043** Component

Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

GAL)		Sep 202	2 Nov2022	May2023 0	ct2023	
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0086717	GFL0071284	GFL0060640
Sample Date		Client Info		05 Oct 2023	04 May 2023	18 Nov 2022
Machine Age	hrs	Client Info		16850	15652	14436
Oil Age	hrs	Client Info		16850	15652	14436
Oil Changed		Client Info		Changed	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	19	9	9
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	<1	0	<1
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	3	<1	<1
Lead	ppm	ASTM D5185m	>40	3	<1	2
Copper	ppm	ASTM D5185m	>330	2	<1	1
Tin	ppm	ASTM D5185m	>15	<1	0	<1
Vanadium	ppm	ASTM D5185m		0	<1	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	3	<1	5
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	83	65	57
Manganese	ppm	ASTM D5185m	0	0	<1	<1
Magnesium	ppm	ASTM D5185m	1010	1312	1047	930
Calcium	ppm	ASTM D5185m	1070	1389	1178	1080
Phosphorus	ppm	ASTM D5185m	1150	1360	1092	957
Zinc	ppm	ASTM D5185m	1270	1700	1325	1187
Sulfur	ppm	ASTM D5185m	2060	4666	3762	3214
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5	4	4
Sodium	ppm	ASTM D5185m		6	5	3
Potassium	ppm	ASTM D5185m	>20	1	0	0
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.4	0.3	0.4
Nitration	Abs/cm	*ASTM D7624	>20	7.4	7.0	8.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.1	18.2	20.6
FLUID DEGRADATION method limit/base current history1 history2						
0						
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.9	14.4	16.2
Oxidation Base Number (BN)	Abs/.1mm mg KOH/g	*ASTM D7414 ASTM D2896	>25 9.8	14.9 7.8	14.4 9.0	16.2 9.8




OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPE	RHES	method	ilmivbase		nistory i	nistory2
Visc @ 100°C	cSt	ASTM D445	15.4	13.5	13.6	13.4

GRAPHS











Certificate L2367

Laboratory Sample No. Lab Number Unique Number : 10700047 Test Package : FLEET

: GFL0086717 : 05982752

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received Diagnosed

: 18 Oct 2023 : 20 Oct 2023 Diagnostician : Sean Felton

GFL Environmental - 932 - Muskego HC

W144 S6400 College Ct. Muskego, WI US 53150

Contact: Brian Schlomann brian.schlomann@gflenv.com T: (262)510-4586

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)