


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
143 (S/N J406723)

Component
Diesel Engine

Fluid
PETRO CANADA DURON HP 15W40 (--- LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PCA0044176	PCA0044270	PCA0044232
Sample Date	Client Info		14 Oct 2023	15 Feb 2023	20 Jul 2022
Machine Age	mls	Client Info	159643	133675	108448
Oil Age	mls	Client Info	25968	25227	23695
Oil Changed	Client Info		Changed	Changed	Changed
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	<1.0	<1.0
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >100	31	28	33
Chromium	ppm	ASTM D5185m >20	2	2	2
Nickel	ppm	ASTM D5185m >4	0	0	0
Titanium	ppm	ASTM D5185m	0	0	0
Silver	ppm	ASTM D5185m >3	0	0	<1
Aluminum	ppm	ASTM D5185m >20	10	9	15
Lead	ppm	ASTM D5185m >40	5	3	5
Copper	ppm	ASTM D5185m >330	<1	<1	2
Tin	ppm	ASTM D5185m >15	<1	<1	1
Antimony	ppm	ASTM D5185m	---	---	---
Vanadium	ppm	ASTM D5185m	0	<1	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	2
Barium	ppm	ASTM D5185m	0	0	0
Molybdenum	ppm	ASTM D5185m	61	59	62
Manganese	ppm	ASTM D5185m	<1	1	<1
Magnesium	ppm	ASTM D5185m	967	928	954
Calcium	ppm	ASTM D5185m	1068	1093	1089
Phosphorus	ppm	ASTM D5185m	1058	941	1012
Zinc	ppm	ASTM D5185m	1230	1237	1284
Sulfur	ppm	ASTM D5185m	2596	2832	3047

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	13	12	10
Sodium	ppm	ASTM D5185m	4	1	<1
Potassium	ppm	ASTM D5185m >20	22	17	37



INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.6	0.5	0.6
Nitration	Abs/cm	*ASTM D7624 >20	11.7	11.7	12.5
Sulfation	Abs/.1mm	*ASTM D7415 >30	24.0	23.3	25.6

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	20.5	19.5	21.8
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	6.60	7.76	6.83









OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.6	13.1	13.1	13.4

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0044176 **Received** : 30 Oct 2023
Lab Number : **05993785** **Diagnosed** : 31 Oct 2023
Unique Number : 10722145 **Diagnostician** : Wes Davis
Test Package : MOB 2

GARY INGRAM GRADING & PAVING
 1767 GRIFFIN SHOULS RD
 DADEVILLE, AL
 US 36853
 Contact: RON INGRAM
 ron.ingram@ingrampaving.com
 T: (256)825-6878
 F:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)