




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
744015-361631

Component
Natural Gas Engine

Fluid
PETRO CANADA DURON GEO LD 15W40 (7 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0081105	GFL0081059	GFL0052588
Sample Date	Client Info		13 Oct 2023	26 Jul 2023	01 May 2023
Machine Age	hrs	Client Info	17910	17749	18586
Oil Age	hrs	Client Info	1200	575	18
Oil Changed	Client Info		Changed	Not Changd	Not Changd
Sample Status			NORMAL	NORMAL	NORMAL

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >50	15	17	16
Chromium	ppm	ASTM D5185m >4	2	2	1
Nickel	ppm	ASTM D5185m >2	<1	<1	0
Titanium	ppm	ASTM D5185m	<1	<1	0
Silver	ppm	ASTM D5185m >3	0	0	0
Aluminum	ppm	ASTM D5185m >9	3	2	1
Lead	ppm	ASTM D5185m >30	2	<1	0
Copper	ppm	ASTM D5185m >35	<1	2	1
Tin	ppm	ASTM D5185m >4	1	1	<1
Vanadium	ppm	ASTM D5185m	0	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 50	11	11	10
Barium	ppm	ASTM D5185m 5	1	2	0
Molybdenum	ppm	ASTM D5185m 50	48	54	54
Manganese	ppm	ASTM D5185m 0	2	2	2
Magnesium	ppm	ASTM D5185m 560	568	686	726
Calcium	ppm	ASTM D5185m 1510	1358	1531	1521
Phosphorus	ppm	ASTM D5185m 780	698	733	705
Zinc	ppm	ASTM D5185m 870	920	1034	1011
Sulfur	ppm	ASTM D5185m 2040	2233	3000	2646

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >+100	8	9	11
Sodium	ppm	ASTM D5185m	4	4	3
Potassium	ppm	ASTM D5185m >20	2	1	<1

INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	0	0.1	0
Nitration	Abs/cm	*ASTM D7624 >20	11.3	11.3	10.5
Sulfation	Abs/.1mm	*ASTM D7415 >30	22.0	21.5	19.2

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	18.8	18.3	17.6
Base Number (BN)	mg KOH/g	ASTM D2896 10.2	5.0	5.3	4.7







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.1	14.7	14.7	14.7

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0081105 **Received** : 01 Nov 2023
Lab Number : **05996209** **Diagnosed** : 02 Nov 2023
Unique Number : 10724569 **Diagnostician** : Wes Davis
Test Package : FLEET

GFL Environmental - 884 - Lake County - Tavares
 321 Southridge Industrial Way
 Tavares, FL
 US 32778
 Contact: JEFF COOPERSMITH

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: