

# **OIL ANALYSIS REPORT**

Sample Rating Trend

**NORMAL** 



# JOHN DEERE E-CAB S125 OT-91 (S/N 23045)

**Diesel Engine** 

PETRO CANADA DURON HP 15W40 (--- G

### DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the

### **Fluid Condition**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

| L)            |          |             |            | Oct2023     |          |          |  |
|---------------|----------|-------------|------------|-------------|----------|----------|--|
| SAMPLE INFOR  | RMATION  | method      | limit/base | current     | history1 | history2 |  |
| Sample Number |          | Client Info |            | PCA0105080  |          |          |  |
| Sample Date   |          | Client Info |            | 17 Oct 2023 |          |          |  |
| Machine Age   | hrs      | Client Info |            | 4400        |          |          |  |
| Oil Age       | hrs      | Client Info |            | 250         |          |          |  |
| Oil Changed   |          | Client Info |            | Changed     |          |          |  |
| Sample Status |          |             |            | NORMAL      |          |          |  |
| CONTAMINA     | TION     | method      | limit/base | current     | history1 | history2 |  |
| -uel          |          | WC Method   | >2.1       | <1.0        |          |          |  |
| Glycol        |          | WC Method   |            | NEG         |          |          |  |
| WEAR METAI    | LS       | method      | limit/base | current     | history1 | history2 |  |
| ron           | ppm      | ASTM D5185m | >51        | 13          |          |          |  |
| Chromium      | ppm      | ASTM D5185m | >11        | <1          |          |          |  |
| lickel        | ppm      | ASTM D5185m | >5         | 0           |          |          |  |
| itanium       | ppm      | ASTM D5185m |            | 0           |          |          |  |
| Silver        | ppm      | ASTM D5185m | >3         | 0           |          |          |  |
| Muminum       | ppm      | ASTM D5185m | >31        | 2           |          |          |  |
| .ead          | ppm      | ASTM D5185m | >26        | 5           |          |          |  |
| Copper        | ppm      | ASTM D5185m | >26        | 2           |          |          |  |
| in            | ppm      | ASTM D5185m | >4         | <1          |          |          |  |
| /anadium      | ppm      | ASTM D5185m |            | 0           |          |          |  |
| Cadmium       | ppm      | ASTM D5185m |            | 0           |          |          |  |
| ADDITIVES     |          | method      | limit/base | current     | history1 | history2 |  |
| Boron         | ppm      | ASTM D5185m |            | 0           |          |          |  |
| Barium        | ppm      | ASTM D5185m |            | 0           |          |          |  |
| Nolybdenum    | ppm      | ASTM D5185m |            | 60          |          |          |  |
| Manganese     | ppm      | ASTM D5185m |            | <1          |          |          |  |
| /lagnesium    | ppm      | ASTM D5185m |            | 1025        |          |          |  |
| Calcium       | ppm      | ASTM D5185m |            | 1119        |          |          |  |
| Phosphorus    | ppm      | ASTM D5185m |            | 1092        |          |          |  |
| inc '         | ppm      | ASTM D5185m |            | 1375        |          |          |  |
| Sulfur        | ppm      | ASTM D5185m |            | 3152        |          |          |  |
| CONTAMINA     | NTS      | method      | limit/base | current     | history1 | history2 |  |
| Silicon       | ppm      | ASTM D5185m | >22        | 5           |          |          |  |
| Sodium        | ppm      | ASTM D5185m | >31        | 0           |          |          |  |
| Potassium     | ppm      | ASTM D5185m | >20        | 0           |          |          |  |
| INFRA-RED     |          | method      | limit/base | current     | history1 | history2 |  |
| Soot %        | %        | *ASTM D7844 | >3         | 0.1         |          |          |  |
| Nitration     | Abs/cm   | *ASTM D7624 | >20        | 6.5         |          |          |  |
| Sulfation     | Abs/.1mm | *ASTM D7415 | >30        | 18.4        |          |          |  |
| FLUID DEGRA   | DATION   | method      | limit/base | current     | history1 | history2 |  |
| Oxidation     | Abs/.1mm | *ASTM D7414 | >25        | 14.9        |          |          |  |
| 0 No (DAD)    |          | AOTA DOCCO  | 0.0        | 0.4         |          |          |  |

9.1

Base Number (BN) mg KOH/g ASTM D2896 9.8

Contact/Location: SPENCER COOPER - TRIFIR



## **OIL ANALYSIS REPORT**







Laboratory Sample No. Lab Number **Unique Number** 

: PCA0105080 : 05996580 : 10724940

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 02 Nov 2023 Diagnosed

: 02 Nov 2023 Diagnostician : Wes Davis Test Package : MOB 1 (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

TRINITAS FARMING 45499 W PANOCHE RD

FIREBAUGH, CA US 93622

Contact: SPENCER COOPER spencer.cooper@trinitasfarming.com

T: (209)493-2999

Contact/Location: SPENCER COOPER - TRIFIR

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: