

OIL ANALYSIS REPORT

Sample Rating Trend





Machine Id 811066

Component **Diesel Engine**

Diesel Engine							
PETRO CANADA DU	RON SHP 15W40 ((GAL)	Jan2023 F	Feb2023 Mar2023 Apr2	023 Apr2023 Jun2023 Aug202	3 Oct2023	
DIAGNOSIS	SAMPLE INFO	RMATION	method	limit/base	e current	history1	history2
ecommendation	Sample Number		Client Info		GFL0097342	GFL0089527	GFL0067940
esample at the next service interval to monitor.	Sample Date		Client Info		31 Oct 2023	22 Aug 2023	05 Jun 2023
lear	Machine Age	hrs	Client Info		4472	4472	3448
Il component wear rates are normal.	Oil Age	hrs	Client Info		4472	543	3191
ontamination	Oil Changed		Client Info		N/A	Changed	N/A
nere is no indication of any contamination in the I.	Sample Status				NORMAL	NORMAL	NORMAL
uid Condition	CONTAMINA	TION	method	limit/base	e current	history1	history2
he BN result indicates that there is suitable	Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
kalinity remaining in the oil. The condition of the	Glycol		WC Method		NEG	NEG	NEG
il is suitable for further service.	WEAR META	LS	method	limit/base	current	history1	history2
	Iron	ppm	ASTM D5185m	>120	4	17	11
	Chromium	ppm	ASTM D5185m	>20	0	<1	<1
	Nickel	ppm	ASTM D5185m	>5	<1	0	<1
	Titanium	ppm	ASTM D5185m	>2	0	0	<1
	Silver	ppm	ASTM D5185m	>2	0	0	0
	Aluminum	ppm	ASTM D5185m	>20	<1	4	<1
	Lead	ppm	ASTM D5185m	>40	0	0	0
	Copper	ppm	ASTM D5185m	>330	0	2	2
	Tin	ppm	ASTM D5185m		<1	<1	<1
	Vanadium	ppm	ASTM D5185m		0	0	0
	Cadmium	ppm	ASTM D5185m		0	0	0
	ADDITIVES		method	limit/base	e current	history1	history2
	Boron	ppm	ASTM D5185m	0	8	5	3
	Barium	ppm	ASTM D5185m	0	0	0	0
	Molybdenum	ppm	ASTM D5185m	60	54	66	61
	Manganese	ppm	ASTM D5185m	0	0	<1	<1
	Magnesium	ppm	ASTM D5185m	1010	880	1046	978
	Calcium	ppm	ASTM D5185m	1070	1012	1167	1120
	Phosphorus	ppm	ASTM D5185m	1150	943	1071	944
	Zinc	ppm	ASTM D5185m	1270	1166	1361	1251
	Sulfur	ppm	ASTM D5185m		2734	3412	3217
	CONTAMINA	NTS	method	limit/base	e current	history1	history2
	Silicon	ppm	ASTM D5185m	>25	4	5	3
	Sodium	ppm	ASTM D5185m		1	4	3
	Potassium	ppm	ASTM D5185m	>20	0	<1	0
	INFRA-RED		method	limit/base	current	history1	history2
	Soot %	%	*ASTM D7844	>4	0.3	0.7	0.5
	Nitration	Abs/cm	*ASTM D7624	>20	6.9	8.6	8.2
	Sulfation	Abs/.1mm			18.9	20.6	20.3
	FLUID DEGRA	ADATION	method	limit/base	current	history1	history2
	Oxidation	Abs/.1mm	*ASTM D7414	>25	14.5	16.2	15.8
				0.0		0.0	7.4

Base Number (BN) mg KOH/g ASTM D2896 9.8

6.8


7.1

7.5



OIL ANALYSIS REPORT

VISUAL



Laboratory Sample No. Lab Number Unique Number Test Package	: WearCheck USA - : GFL0097342 : 05997268 : 10725628 : FLEET contact Customer Serv	Received Diagnose Diagnost	l : 02 ed : 03 ician : We	Nov 2023 Nov 2023 s Davis	3 GFL E	Conta	30 Deerg Midl	rove Roa lothian, V US 2311 in Umphl
	Jan 16/22 Jan 16/22 Feb22/23 Mart 5/22 Mart 5/22 Mart 5/22 Mart 5/22 Mart 5/22 Mart 5/22 Mart 5/22 Mart 6/22 Mart 6/22 M	Apr4/23	Jun5/23	4 sadmul ase8 0	0-	Apr4/23 Apr4/23	Jun5/23 -	Aug22/23
	19 18 Abnormal 17 16 Base 0,0015 41 41 4			10 (b/HOX bu) Base Base (b/HOX bu) Base (b/HOX bu) (b/HOX bu) (b/H	0 Base			
	5 0 EZ91 EZ91 EZ72 F Viscosity @ 100°C	Apr4/23	Jun5/23 Aug22/23	0ct31/23	Base Numbe	r		
	25 - Copper lead 20 - Lin 10 - Lin							
	Non-ferrous Meta	Apr4/23	Jun5/23	0ct31/23				
Aur	25 15 10 5							
Aug22/23	GRAPHS Ferrous Alloys							
	FLUID PROPE Visc @ 100°C	cSt	method ASTM D445	limit/base	current 13.4	history 14.0		history2 3.8
	Emulsified Water Free Water	scalar scalar	*Visual *Visual	>0.2	NEG NEG	NEG NEG	Ν	IEG IEG
Aug22/23 0ct31/23	Appearance Odor	scalar scalar	*Visual *Visual	NORML NORML	NORML NORML	NORML		IORML
ug22/23	Sand/Dirt	scalar scalar	*Visual	NONE	NONE	NONE		IONE IONE
	Silt Debris	scalar	*Visual *Visual	NONE NONE	NONE NONE	NONE		IONE
	Yellow Metal Precipitate	scalar scalar	*Visual *Visual	NONE NONE	NONE NONE	NONE NONE		IONE