


# **OIL ANALYSIS REPORT**

## **Sample Rating Trend**



NORMAL



Machine Id 910017 Component

**Diesel Engine** 

PETRO CANADA DURON SHP 15W40 (12 GAL)

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

#### Wear

Metal levels are typical for a new component breaking in.

## Contamination

There is no indication of any contamination in the


### **Fluid Condition**


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

GAL)						
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0098102	GFL0088523	GFL0088554
Sample Date		Client Info		01 Nov 2023	03 Oct 2023	22 Aug 2023
Machine Age	hrs	Client Info		594	594	594
Oil Age	hrs	Client Info		372	259	392
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINA	TION	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METAI	LS	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>90	7	5	7
Chromium	ppm	ASTM D5185m	>20	<1	1	1
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m	>2	0	<1	0
Silver	ppm	ASTM D5185m	>2	0	<1	0
Aluminum	ppm	ASTM D5185m	>20	2	2	2
Lead	ppm	ASTM D5185m	>40	0	<1	0
Copper	ppm		>330	<1	<1	<1
Tin	ppm	ASTM D5185m	>15	0	<1	0
Vanadium	ppm	ASTM D5185m	7.0	0	0	0
Cadmium	ppm	ASTM D5185m		<1	<1	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	4	5	6
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	64	62	59
Manganese	ppm	ASTM D5185m	0	0	<1	<1
Magnesium	ppm	ASTM D5185m	1010	949	1119	913
Calcium	ppm	ASTM D5185m	1070	1167	1343	1139
Phosphorus	ppm	ASTM D5185m	1150	959	1141	1042
Zinc	ppm		1270	1268	1498	1243
Sulfur	ppm	ASTM D5185m	2060	3628	3965	3521
CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	3	3	4
Sodium	ppm	ASTM D5185m		0	3	2
Potassium	ppm	ASTM D5185m	>20	6	7	8
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>6	0.6	0.3	0.4
Nitration	Abs/cm	*ASTM D7624	>20	6.7	5.9	6.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.9	17.5	18.0
FLUID DEGRA	DATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.0	13.2	13.5
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.9	8.9	8.6



## **OIL ANALYSIS REPORT**








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPE	RTIES	method				history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.2	14.4	14.3

## **GRAPHS**













Certificate L2367

Report Id: GFL017 [WUSCAR] 05997295 (Generated: 11/03/2023 13:54:55) Rev: 1

Laboratory Sample No. Lab Number Unique Number : 10725655 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0098102 : 05997295

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received Diagnosed

: 02 Nov 2023 : 03 Nov 2023 Diagnostician : Wes Davis

148 Stone Park Court Durham, NC US 27703 Contact: William Russel

william.russell@gflenv.com T:

F: (919)598-1852

GFL Environmental - 017 - Durham

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Submitted By: Shane Parks