


OIL ANALYSIS REPORT

Sam



NORMAL



Machine Id 224102 Component

Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

LIR)		Sep 2021	0et2022	Dec2022 Jan2023	Nov2023	
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0078601	GFL0065648	GFL0065617
Sample Date		Client Info		01 Nov 2023	30 Jan 2023	28 Dec 2022
Machine Age	hrs	Client Info		19981	18490	18290
Oil Age	hrs	Client Info		0	1200	600
Oil Changed		Client Info		Not Changd	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	20	9	29
Chromium	ppm	ASTM D5185m	>20	<1	<1	2
Nickel	ppm	ASTM D5185m	>4	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	<1	0	1
Lead	ppm	ASTM D5185m	>40	1	<1	4
Copper	ppm	ASTM D5185m	>330	1	2	2
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	11	28	22
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	63	60	69
Manganese	ppm	ASTM D5185m	0	0	0	<1
Magnesium	ppm	ASTM D5185m	1010	922	754	869
Calcium	ppm	ASTM D5185m	1070	1091	1073	1318
Phosphorus	ppm	ASTM D5185m	1150	978	889	957
Zinc	ppm	ASTM D5185m	1270	1236	1065	1217
Sulfur	ppm	ASTM D5185m	2060	2877	2801	3292
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	3	2	4
Sodium	ppm	ASTM D5185m		2	0	2
Potassium	ppm	ASTM D5185m	>20	0	2	0
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.3	0.3	0.4
Nitration	Abs/cm	*ASTM D7624	>20	9.7	9.0	10.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.4	20.7	21.8
FLUID DEGRADATION method limit/base current history1 history2						
Oxidation	Abs/.1mm	*ASTM D7414	>25	10.0	18.6	20.2
	AUS/- IIIIIII			19.0	10.0	∠U.∠
Base Number (BN)	mg KOH/g	ASTM D2896		19.0 8.5	7.6	7.8



OIL ANALYSIS REPORT





Viscosit	y @ 100°0			
18 - Abnormal				
17-				
0015 Base Base				
₹3 14				
13 - Abnormal				
12				
Sep10/21.	Oct18/22	Jec28/22	Jan 30/23	
Sep	Octl	Dec	Jan	


VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPI	ERTIES	method				history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.2	13.6	14.0

GRAPHS













Laboratory

Sample No. Lab Number Unique Number : 10727078 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0078601 : 05998718

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received Diagnosed

: 06 Nov 2023 : 06 Nov 2023 Diagnostician : Wes Davis

GFL Environmental - 152 - Jacksonville

7580 PHILIPS HWY Jacksonville, FL US 32256 Contact: Chris Smith

chris.smith@gflenv.com T: (904)252-0013

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: GFL152 [WUSCAR] 05998718 (Generated: 11/07/2023 11:49:25) Rev: 1

Submitted By: admin GFL152 - Chris Smith