




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
910015

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0092718	GFL0072356	GFL0048883
Sample Date	Client Info		02 Nov 2023	24 Jan 2023	30 Jun 2022
Machine Age	mls	Client Info	7393	7393	0
Oil Age	mls	Client Info	494	7393	260
Oil Changed	Client Info		Not Changed	Not Changd	Not Changed
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	<1.0	<1.0
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m	>165	58	50	54
Chromium	ppm	ASTM D5185m	>5	2	2	3
Nickel	ppm	ASTM D5185m	>4	2	0	<1
Titanium	ppm	ASTM D5185m	>2	0	0	<1
Silver	ppm	ASTM D5185m	>2	<1	0	0
Aluminum	ppm	ASTM D5185m	>20	4	5	8
Lead	ppm	ASTM D5185m	>150	0	<1	0
Copper	ppm	ASTM D5185m	>90	15	1	1
Tin	ppm	ASTM D5185m	>5	1	<1	<1
Antimony	ppm	ASTM D5185m		---	---	---
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0

ADDITIVES

	method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m	0	7	3	4
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	62	62	62
Manganese	ppm	ASTM D5185m	0	1	<1	<1
Magnesium	ppm	ASTM D5185m	1010	920	929	964
Calcium	ppm	ASTM D5185m	1070	1085	1084	1215
Phosphorus	ppm	ASTM D5185m	1150	988	980	997
Zinc	ppm	ASTM D5185m	1270	1306	1183	1288
Sulfur	ppm	ASTM D5185m	2060	2653	3185	3278

CONTAMINANTS

	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>35	8	6	6
Sodium	ppm	ASTM D5185m		1	3	6
Potassium	ppm	ASTM D5185m	>20	6	8	13

INFRA-RED



	method	limit/base	current	history1	history2	
Soot %	%	*ASTM D7844	>7.5	2.2	2.1	2.1
Nitration	Abs/cm	*ASTM D7624	>20	12.1	13.2	13.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	25.9	27.4	28.0

FLUID DEGRADATION

	method	limit/base	current	history1	history2	
Oxidation	Abs/.1mm	*ASTM D7414	>25	22.2	23.9	23.1
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	6.0	5.4	6.0







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	13.5	14.0	14.1

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0092718 **Received** : 06 Nov 2023
Lab Number : **05998792** **Diagnosed** : 07 Nov 2023
Unique Number : 10727152 **Diagnostician** : Wes Davis
Test Package : FLEET

GFL Environmental - 005 - Wilson/Tri-East (CNG)
 2810 Contentnea Road S
 Wilson, NC
 US 27893-8501
 Contact: SPENCER LIGGON
 spencer.liggon@gflenv.com
 T: (800)207-6618
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)